

Transverse prestressing of prestressed laminated wood bridge decks

Autor(en): **Batchelor, B. deV. / Dalen, K. van / Taylor, R.J.**

Objekttyp: **Article**

Zeitschrift: **IABSE congress report = Rapport du congrès AIPC = IVBH
Kongressbericht**

Band (Jahr): **12 (1984)**

PDF erstellt am: **23.05.2024**

Persistenter Link: <https://doi.org/10.5169/seals-12256>

Nutzungsbedingungen

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

Haftungsausschluss

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.

Transverse Prestressing of Prestressed Laminated Wood Bridge Decks**B. deV. BATCHELOR**Prof. of Civil Eng.
Queen's Univ.
Kingston, ON, Canada**K. Van DALEN**Prof. of Civil Eng.
Queen's Univ.
Kingston, ON, Canada**R.J. TAYLOR**Res. Eng.
Ontario MTC
Downsview, ON, Canada

A form of construction which is well suited to short span bridges is the nailed-laminated wood deck. However, experience has shown the load distribution of this type of deck is severely impaired with time due to rusting and ultimate failure of the nails. A method (1) has been developed for the rehabilitation of nailed laminated wood decks which involves introduction of transverse prestressing. This method has also been successfully applied to new construction. Initially, no standard method of design existed for such an application of prestress to wood systems and studies have been undertaken (1) to assess the behaviour of such systems and to determine the appropriate values of structural parameters for use in analysis and design. As shown in the figure, the details of the prestressing system vary depending on whether it is applied to rehabilitation of existing structures or to new construction. Typical details are provided in the Ontario Highway Bridge Design Code (2) which includes a section on prestressed wood systems.

Laboratory and field studies have been conducted on the system (1). The objective of the laboratory studies was the determination of orthotropic plate parameters and prestress losses. The main variables were type of wood (hem-fir, white pine and red pine), type of wood treatment and level of initial prestress. Tests were conducted on laminated beams and plates and on axially loaded prisms formed from laminates. The results of these investigations have also been reflected in the provisions of Reference (2).

The prestressed laminated wood deck lends itself to prefabrication. Its superior load distribution over that of existing conventional nailed laminated decks has been demonstrated (1) as shown in the figure. The Hebert Creek Bridge which was rehabilitated in 1976, has been monitored regularly, and has confirmed that the system is feasible and economical. This has also been confirmed at other sites in Ontario.

REFERENCES

1. Taylor, R.J., Batchelor, B.deV. and Van Dalen, K., "Prestressed Wood Bridges", Procs. International Conference on Short and Medium Span Bridges", Vol. 2, August 8-12, Toronto, Ontario, pp: 203-218.
2. Ontario Highway Bridge Design Code, Ontario Ministry of Transportation and Communications, Downsview, Ontario, 1983.

1118

TRANSVERSE PRESTRESSING OF LAMINATED WOOD BRIDGE DECKS

Existing Nailed Decks

Problems - Nails are susceptible to repeated loads causing delamination. This reduces load carrying capacity & life expectancy, and increases maintenance costs.

Typical X-section Solution - Transverse Prestressing

RESEARCH AND CONSTRUCTION

PLATE TWIST TEST

TEST RIG

Load Testing

Other Applications

FOX LAKE Bridge New prestressed laminated wood rigid frame. Built 1981, Sudbury, Ontario.

AGUASABON R. Bridge New transversely laminated, prestressed wood. Segmental Construction. Terrace Bay, Ontario 1983.

VICTORIA ISLAND Bridge Deck replacement with prestressed wood panels. Ontario Hydro Ottawa, 1984.

CONCLUSION - PRESTRESSED WOOD DECKS FEASIBLE

Graph: Shear Modulus vs Average Prestress

Avg. Prestress (kPa)	White Pine (MPa)	Hem-Fir (MPa)	Red Pine (MPa)
300	~300	~300	~300
500	~400	~400	~400
700	~450	~450	~450
900	~500	~500	~500

Graph: % Stress vs Time Weeks