

Tests and analysis on the pedestrian suspended-slab bridge

Autor(en): **Murakami, Yoshimaru / Nakazawa, Takao / Sezaki, Mitsuhiro**

Objekttyp: **Article**

Zeitschrift: **IABSE congress report = Rapport du congrès AIPC = IVBH
Kongressbericht**

Band (Jahr): **12 (1984)**

PDF erstellt am: **23.05.2024**

Persistenter Link: <https://doi.org/10.5169/seals-12257>

Nutzungsbedingungen

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

Haftungsausschluss

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.



Tests and Analyses on the Pedestrian Suspended-Slab Bridge

Yoshimaru MURAKAMI

Prof. Dr.
Miyazaki Univ.
Miyazaki, Japan

Takao NAKAZAWA

Assoc. Prof., Dr.
Miyazaki Univ.
Miyazaki, Japan

Mitsuhiko SEZAKI

Res. Assoc.
Miyazaki Univ.
Miyazaki, Japan

A suspended-slab bridge (Spannband-Brücke) is essentially the same structural system as the suspended-roof in buildings. This type bridge is made by spanning of tendons which are lined with reinforced concrete to provide the rigidity as slab. Its advantage is not only applicable to long span, but also unnecessary to use the elements such as main towers, hangers and stiffened members in a conventional suspension bridge, and almost free from the maintenance works. However, these bridges are very few, because we have only an insufficient knowledge on their characteristics of deflection or vibration and the effects of cracking about such a structure.

For these reasons, authors have conducted following experiments; firstly, to construct two model bridges of this type for pedestrians with a span of 10m and a width of 0.7m which were designed by using the span/sag ratio, 100 (Type A) and 50 (Type B), respectively; secondly, to investigate the behaviour of these bridges due to temperature variations and pedestrian-actions; thirdly, to measure the cracks relating to the sand-loading test; and finally, to execute the shaking test.

The main points obtained from the experimental results are summarized as follows; 1) cracks appeared in the slab near the bridge seat due to the mere change of temperature; 2) when static loading up to about 1.0t/m, which is 4.1 times as large as the design load, were applied, the number of cracks appeared in the slab was 77 in Type A per span length 10m (mean crack spacing $\ell_{\text{mean}}=13\text{cm}$; maximum crack width $w_{\text{max}}=0.8\text{mm}$ appeared near the bridge seat); and 71 in Type B ($\ell_{\text{mean}}=14\text{cm}$, $w_{\text{max}}=0.7\text{mm}$), respectively, but all these cracks closed after removing the load; 3) although the vibration mode was close to bending vibration in the case of no crack or few cracks, the mode approached to longitudinal vibration of tendons as the number of cracks were increasing, and the resonance frequency had a tendency to decrease; 4) smaller span/sag ratio is not only favorable for all mechanical properties such as deflection, vibration, cracking et al., but also economical.

TESTS & ANALYSES ON PEDESTRIAN SUSPENDED SLAB BRIDGE

