

**Zeitschrift:** IABSE reports = Rapports AIPC = IVBH Berichte  
**Band:** 54 (1987)

**Artikel:** Numerical models for the non-linear analysis of prestressed concrete frames  
**Autor:** Calvi, Gian Michele / Gobetti, Armando  
**DOI:** <https://doi.org/10.5169/seals-41934>

### **Nutzungsbedingungen**

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

### **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

### **Terms of use**

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

**Download PDF:** 11.07.2025

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**

## Numerical Models for the Non-Linear Analysis of Prestressed Concrete Frames

Modèles numériques pour l'analyse non-linéaire de cadres en béton précontraint

Numerische Modelle für die nichtlineare Berechnung von Spannbetonrahmen

**Gian Michele CALVI**  
Researcher  
ISMES  
Bergamo, Italy



G.M. Calvi, born 1957, received his M.S. in structural engineering from the University of California, Berkeley, in 1985 and recently completed the requirements for his Doctorate degree at the Politecnico di Milano. He has been involved in research related to seismic behaviour of reinforced masonry and prestressed concrete structures.



**Armando GOBETTI**  
Assoc. Prof.  
University of Pavia  
Pavia, Italy

A. Gobetti, born 1947, graduated at the University of Pavia in 1971, where he is presently Associate Professor of Dynamics of Structures. His research fields concern the numerical techniques for the solution of structural problems.

### SUMMARY

After a brief overview of the models currently used for prestressed concrete structures, a model originally developed by the authors is discussed in detail. Its main goal seems to be the simplicity in which shear deformations and slippage of the cables are considered.

### RÉSUMÉ

Après avoir passé en revue les modèles actuellement employés pour les structures en béton précontraint, les auteurs présentent leur propre modèle. Le résultat le plus important que l'on peut attendre de ce modèle est la simplicité dans l'expression de la déformation due à l'effort tranchant et de l'écoulement des câbles.

### ZUSAMMENFASSUNG

Nach einer kurzen Übersicht über die Modelle, die heute für Spannbeton gebräuchlich sind, wird ein von den Autoren entwickeltes Modell im einzelnen besprochen. Das wichtigste Ergebnis ist, dass Schubverformung und Kabelschlupf sehr einfach behandelt werden können.



## 1. FOREWORD

The design of prestressed concrete structures must satisfy the requirements of safety and serviceability, as all other kinds of structures.

While this can be accomplished in most cases by following approximate or empirical procedures, it is also desirable to have refined models which can trace the structural response throughout their elastic, cracking, inelastic and ultimate ranges.

The use of these models can be either providing a firmer basis for the codes and analyzing unusual and complex structures.

The purpose of this paper is twofold: first a brief overview of the currently used models is given, then some more details are given about a model developed by the authors.

## 2. PROBLEMS IN MODELLING PRESTRESSED CONCRETE FRAMES

When dealing with prestressed members any model should be evaluated with respect to some important and peculiar problems.

Time dependent effects, due either to load history, temperature history, creep, shrinkage and aging of concrete and relaxation of the prestressing cables, have the outmost importance because of the character of imposed deformation of the prestressing action.

Bond between tendons, mortar and concrete is a qualifying point: refined model should give the possibility of simulating bonded and unbonded tendons, and in the former case should incorporate a law for the progressive deterioration and failure of bond connections.

Shear deformations and effects of the prestressing action on shear cannot always be neglected, particularly when dealing with deep beams.

Planarity of the section is not guaranteed due to shear and torsions, and is not respected at all after some slippage between cables and concrete has occurred.

Connections between elements, mainly beam-column connections, may create problems to some models, effective for one-dimensional structures.

The constitutive relations are sometime based on well established laws for concrete and steel, sometimes on the contrary are obtained through heuristic corrections of the usual relations for concrete beams.

Finally computer time and memory may be very penalizing for too refined or bad conditioned elements.

## 3. CURRENT MODELS

Models based on quite different ideas are presently implemented to simulate the behavior of PC beams. The most commonly used ones will be briefly presented in what follows.

### 3.1 Traditional beam elements with corrections

This is conceptually the simplest and most heuristic approach /2/. The usual moment-rotation relations are used, correcting at each time step the stiffness of the elements in order to take into account the actual non-linearity.

The prestressing action is introduced as an external force, but the reduction in stiffness keeps it equivalent to an imposed deformation. The sections are considered to remain plane, bond and shear are not explicitly taken into account.

Most of the job consist in getting the right correction factors for cracking, time dependent effects, tension stiffening.

### 3.2. Integration of sectional M- $\phi$ relations

A second approach is based on the use of sectional results, obtained normally through programs which divide any section into layers with different stress-strain relations. Equilibrium and planarity of the section are then imposed to get moment-curvature relations /7/.

The prestressing action is taken into account prestressing some steel layers, bond is supposed to be perfect, time dependent effects are usually neglected. A number of choices is then possible to get the overall stiffness of a beam element:

1. Each beam can be identified by one or more sections, using constant, linear or higher order variation of the stiffness properties along the member;
2. The moment-curvature relations can be piecewise linearized, or the actual M -  $\phi$  can be used and the stiffness of each section computed at each step within the F.E. analysis /1/. In this case the procedure may be very time consuming.

### 3.3. Layer and filament models

A beam element is decomposed in a number of straight layers or filament each of them with a monodimensional stress-strain law which can take into account also time dependent effects.

Pretensioned, bonded and unbonded postensioned cables can be simulated, shear deformations are neglected.

The elements cross sections should have a symmetry in the case of layers models, can be of any shape in the case of filament models.

The tendons are straight, but not necessarily horizontal within the element /11/.

## 4. BIDIMENSIONAL LAYERS MODEL

This model, recently implemented by the authors, differs from the layer model mainly because of the layers are here modeled as plane stress elements instead of one-dimensional.

The advantages of such a model may be summarized as follows:

1. the shear deformations are considered, which is particularly important for deep beams.
2. It is possible to take into account the interactions between axial action, shear and bending moment.
3. The sections can assume up to a second order polynomial shape.
4. The number of layers is much smaller than in the case of a monodimensional layer model.

### 4.1. Analytical Formulation

The adopted approach is the Displacement Finite Element Formulation.

The displacement fields are defined over a bidimensional domain, subdivided into strips through the height of the beam.

The strain-displacement relations for the Timoshenko beam theory may be written as:

$$\begin{aligned}\epsilon_{RR} &= -S \frac{\partial \theta}{\partial R} + \frac{\partial u}{\partial R} \\ \epsilon_{RS} &= -\theta + \frac{\partial v}{\partial R}\end{aligned}\tag{1}$$

Where R and S are coordinates related to a sectional reference system, which may vary along the beam because of the variability in the shape of the cross section; u, v and  $\theta$  are the generalized displacement components, according to a classical Lagrangian formulation, referred to an absolute reference system.



The commonly used Bernoulli-Navier formulation, which requires the planarity of the sections, assumes:

$$\theta = \frac{dv}{dR} \quad (2)$$

and consequently equations (1) assumes the form:

$$\begin{aligned} \epsilon_{RR} &= -S \frac{d^2v}{dR^2} + \frac{du}{dR} \\ \epsilon_{RS} &= 0 \end{aligned} \quad (3)$$

This formulation requires the continuity in  $C^1$  for the discrete variables in the shape functions: they have to be at least of the third order in  $R$  for  $v$  and of the first order for  $u$  (see table 1).

The use of the Timoshenko theory gives many advantages and one problem:

- the shape functions have to be continuous in  $C^0$ , they can be the same for  $u$ ,  $v$  and  $\theta$  (see table 1).
- Three nodes elements can be used, so that curved beams can be represented, the layers can have curvilinear borders, sensible modifications in the cross section shape do not give problems.
- The shear deformations are directly taken into account.
- The problem is that the strain tensor components are not of the same order, so that the shear effects are overestimated when the height of the beam becomes smaller and smaller.

This difficulty has been successfully overjumped by fictitiously reducing the degree of  $\epsilon_{RS}$  and setting the  $\epsilon_{RS}$  and the  $\epsilon_{RS}$  reduced at the same values at the Gauss integration points.

For the prestressing steel layers the strain displacement relations are modified as follows:

$$\begin{aligned} \epsilon_{RR} &= -\frac{\partial\theta}{\partial R} + \frac{\partial u}{\partial R} + \epsilon_0 + \frac{\partial\Delta u}{\partial R} \\ \epsilon_{RS} &= -\theta + \frac{\partial v}{\partial R} \end{aligned} \quad (4)$$

Where  $\epsilon_0$  is the initial strain due to prestressing and  $\Delta u$  is the slippage between cable and concrete after the bond has been destroyed.

#### 4.2. Constitutive Equations

The constitutive equations have to be biaxial for concrete and steel and have to treat the bond between steel and concrete.

Concrete. The relations presented by Kupfer and Gerstle /8/ have been used. They separate the hydrostatic and deviatoric behavior:

$$\begin{aligned} \sigma_0 &= 3K \epsilon_0 \\ \sigma_0 &= 2G \gamma_0 \end{aligned} \quad (5)$$

finding a very good correlation between the experimental results and the following equations:

$$\begin{aligned} G_S/G_0 &= 1 - a (\tau_0/f_{cu})^m \\ G_T/G_0 &= \frac{(G_S/G_0)^2}{m - G_S/G_0 (m-1)} \\ K_S/K_0 &= G_S/G_0 e^{(c\gamma_0)^p} \\ K_T/K_0 &= \frac{G_T/G_0}{e^{-(c\gamma_0)^p} (1 - p(c\gamma_0)^p)} \end{aligned} \quad (6)$$



where  $G_S$  and  $K_S$  are the secant moduli,  
 $G_T$  and  $K_T$  are the tangent moduli,  
 $G_0$ ,  $K_0$ ,  $a$ ,  $m$ ,  $c$ , and  $p$  are constants given as a  
function of ultimate monoaxial strength  $f_{cu}$

The biaxial strength is then given by the expressions:

$$\text{compression-compression } (\sigma_1/f_{cu} + \sigma_2/f_{cu})^2 + \sigma_1/f_{cu} + 3.65 \sigma_2/f_{cu} = 0$$

$$\text{compression-tension } \sigma_2/f_{tu} = 1 + 0.8 \sqrt[3]{\sigma_1/f_{cu}} \quad (7)$$

$$\text{tension-tension } \sigma_2 = f_{tu} = 0.64 \sqrt[3]{f_{cu}^2}$$

The material stiffness matrix is:

$$4G \begin{bmatrix} 1 & \frac{3K-2G}{2(3K+G)} & 0 \\ \frac{3K+G}{3K+4G} & \frac{3K-2G}{2(3K+G)} & 0 \\ 0 & 0 & \frac{3K+4G}{4(3K+G)} \end{bmatrix} \quad (8)$$

setting  $\sigma_y = 0$  the final relations for concrete are obtained:

$$\begin{bmatrix} \sigma_{RR} \\ \sigma_{RS} \end{bmatrix} = \begin{bmatrix} \frac{9KG}{3K+D} & 0 \\ 0 & G \end{bmatrix} \times \begin{bmatrix} \epsilon_{RR} \\ \epsilon_{RS} \end{bmatrix} \quad (9)$$

Steel. The Von Mises plastic potential has been used, with an isotropic hardening taken from the CEB quintic for prestressing steel:

$$\epsilon_S = 0.823 \left( \frac{\sigma_S}{f_{y0.2}} - 0.77 \right)^5 \quad \sigma_S > 0.7 \frac{f_{y0.2}}{E_S} \quad (10)$$

$$\epsilon_S = \frac{\sigma_S}{E_S} \quad \sigma_S < 0.7 \frac{f_{y0.2}}{E_S}$$

By conformity and normality the following expression for the plastic velocity of deformation is obtained:

$$\dot{\epsilon}_{ij}^{(p)} = \bar{H} \frac{\partial f}{\partial \sigma_{kl}} \dot{\sigma}_{kl} \frac{\partial f}{\partial \sigma_{ij}} \quad (11)$$

where

$$\bar{H} = \frac{1}{\frac{\partial f}{\partial \epsilon_{mn}^{(P)}} + \frac{\partial f}{\partial \chi} \frac{\partial \chi}{\partial \epsilon_{mn}^{(P)}} \frac{\partial f}{\partial \sigma_{mn}}}$$

and

$$f(\sigma_{ij}, \dot{\epsilon}_{ij}^{(P)}, \chi(\dot{\epsilon}_{ij}^{(P)})) = 0 \quad (12)$$

by consistency.



With some manipulation the material stiffness matrix is obtained:

$$\begin{bmatrix} \Delta\sigma_{RR} \\ \Delta\sigma_{RS} \end{bmatrix} = \frac{1}{\frac{4\bar{H}}{9G} \sigma_{RR}^2 + \frac{4\bar{H}}{E} \sigma_{RR}^2 + \frac{1}{EG}} \begin{bmatrix} 4\bar{H}\sigma_{RS}^2 + \frac{1}{G} & -\frac{3}{4}\bar{H}\sigma_{RR}\sigma_{RS} \\ -\frac{4}{3}\bar{H}\sigma_{RR}\sigma_{RS} & \frac{4}{9}\bar{H}\sigma_{RR}^2 + \frac{1}{E} \end{bmatrix} \begin{bmatrix} \Delta\epsilon_{RR} \\ \Delta\epsilon_{RS} \end{bmatrix} \quad (13)$$

with

$$\bar{H} = 9.2587534 \frac{S \sqrt{(\epsilon_p/0.823)^4}}{f_{y0.2}^2 \sigma_{RR} (0.7 + \sqrt{\epsilon_p/0.823})}$$

For the ordinary steel hardening has been neglected because it is not usually reached: the ultimate strain of the prestressing steel is normally lower than the hardening strain of the ordinary steel.

Its constitutive equation is consequently simply elastic-perfectly plastic.

**Bond.** The bond between steel and concrete is presently considered as rigid-plastic, but it could be easily transformed in a multi-linear relation.

At every step the stresses at the border of the concrete layers are checked at the joint position: if a failure occurs the bond ties are supposed to be broken.

As a consequence the height variable  $S$  for the steel layer is not any more taken with reference to the N.A. of the section, but with reference to the N.A. of the layer. In such a way the moment of inertia of the steel layer is not any more contributing to the whole section moment of inertia.

Moreover a new unknown variable  $\Delta u$  (eq.2) is considered, which is the displacement of the steel layer at the joint where the failure has occurred.

Of course this means that a new row and a new column are inserted in the stiffness matrix.

Two different strategies are possible, depending on the meaning of  $\Delta u$ : it may be taken as the total displacement of the cable joint or as the displacement of the cable joint with respect to the deformed position of the section. To clarify the ideas let's consider a two elements, three joints, two layers example in the simpler formulation.

The stiffness matrix can be written as follows:

$$\begin{bmatrix} F_{u1} \\ F_{v1} \\ F_{\theta1} \\ F_{u2} \\ F_{v2} \\ F_{\theta2} \\ F_{u3} \\ F_{v3} \\ F_{\theta3} \\ F_{\Delta u} \end{bmatrix} = \begin{bmatrix} K_{1,1} & 0 & 0 & K_{1,4} & 0 & 0 & 0 & 0 & 0 & K_{1,10} \\ & K_{2,2} & K_{2,3} & 0 & K_{2,5} & K_{2,6} & 0 & 0 & 0 & 0 \\ & & K_{3,3} & 0 & K_{3,5} & K_{3,6} & 0 & 0 & 0 & 0 \\ & & & K_{4,4} & 0 & 0 & K_{4,7} & 0 & 0 & 0 \\ & & & & K_{5,5} & K_{5,6} & 0 & K_{5,8} & K_{5,9} & 0 \\ & & & & & K_{6,6} & 0 & K_{6,8} & K_{6,9} & 0 \\ & & & & & & K_{7,7} & 0 & 0 & 0 \\ & & & & & & & K_{8,8} & K_{8,9} & 0 \\ & & & & & & & & K_{9,9} & 0 \\ & & & & & & & & & K_{10,10} \end{bmatrix} \begin{bmatrix} u_1 \\ v_1 \\ \theta_1 \\ u_2 \\ v_2 \\ \theta_2 \\ u_3 \\ v_3 \\ \theta_3 \\ \Delta u \end{bmatrix} \quad (14)$$

Some significant terms of the stiffness matrix are explicitly given in table 2, before and after the bond failure at joint 2.

## 5. CONCLUSIONS

The main points to be considered when dealing with modeling P.C. frames are discussed, showing that a choice should be operated case by case to take into account the most important effects and to disregard the others.

An original model is presented: it seems to be a good compromise between

simplicity of calculation and refinement in the material modeling. The model deals satisfactorily with the problems of bond, shear, connections and constitutive relationships, but presently disregards the time dependent effects.

Many simulations of different structure are needed in order to check the effectiveness of the model; then further refinements might be implemented. The most important of them seem to be to consider a multilinear law for bond and to take into account time dependent effects.

A particular problem deals with the constitutive equations for concrete, extensively discussed in /3/; in the present model it seems to be necessary to take into account the effect of confinement due to steel.

6. REFERENCES

- /1/ CALVI G.M., Cyclic Behavior of Partially Prestressed Continuous Beams - M.S. thesis, Div. of Struct. Eng. and Struct. Mech., Dept. of Civ. Eng., University of California, Berkeley, May, 1985
- /2/ CAUVIN A., Non linear Analysis of Prestressed Concrete Continuous Beams and Frames - Proceedings, Int. Symp. on Non-linearity and Continuity in Prestressed Concrete, Un. of Waterloo, Ontario, Canada, July, 1983
- /3/ C.E.B. TASK GROUP 6, Concrete under Multiaxial States of Stress. Constitutive Equations for Practical Design - Bull. N.156, June, 1983
- /4/ CRISFIELD M.A., A Quadratic Mindlin Element using Shear Constraints - Computer and Structures, 1984, 833-852
- /5/ GOBETTI A., A Finite Element Model for Geometrically Nonlinear Elastoplastic Plane Frame Structures, Rep. N. 25, Dept. of Struct. Mech., Un. of Pavia, Italy, 1986
- /6/ HUGHES T.J.R., The Heterosis Finite Element Methods for Plate Bending - Computers and Structures, 1978, 445-450
- /7/ KABA, S.A., MAHIN, S.A, Interactive Computer Analysis Methods for Predicting the Inelastic Behavior of Sections, Rep. No. UCB/EERC-83/18, EERC, Univ. of California, Berkeley, July 1983
- /8/ KUPFER, H.B. and GERSTLE, K.H., Behavior of concrete under biaxial stresses, Journ. of the Eng. Mech. Div., ASCE, VOL.99, N. EM4, Aug., 1973
- /9/ MINDLIN R.D., Influence of Rotatory Inertia and Shear on Flexural Motions of Isotropic Elastic Plates , Journ. of App. Mech., 1951, 31-38
- /10/ PRATHAP G., An Optimally Constrained 4-Node Quadrilateral Thin Plate Bending Element - Computers and Structures, 1984, 789-794
- /11/ SCORDELIS A., Analytical Models for Non linear Material, Geometric and Time-Dependent Effects - Proc., Int. Symp. on Nonlinearity and Continuity in Prestressed Concrete, Un. of Waterloo, Ontario, Canada, July 1983.

$N_{v,1} = \frac{1}{2} - \frac{3}{2} \frac{R}{l} + 2 \frac{R^3}{l^3}$ $N_{v,2} = \frac{1}{2} + \frac{3}{2} \frac{R}{l} - 2 \frac{R^3}{l^3}$ $N_{\theta,1} = \frac{1}{8} - \frac{R}{4} - \frac{R^2}{2l} + \frac{R^3}{l^3}$ $N_{\theta,2} = -\frac{1}{8} - \frac{R}{4} + \frac{R^2}{2l} + \frac{R^3}{l^3}$ $N_{u,1} = \frac{1}{2} - \frac{R}{l}$ $N_{u,2} = \frac{1}{2} + \frac{R}{l}$	$N_{u,v,\theta,1} = \frac{2R^2}{l^2} - \frac{R}{l}$ $N_{u,v,\theta,2} = \frac{2R^2}{l^2} + \frac{R}{l}$ $N_{u,v,\theta,3} = 1 - \frac{4R^2}{l^2}$

Table 1 - shape functions according to the Bernoulli-Navier and the Timoshenko formulations



	Before bond failure at joint 2	After bond failure at joint 2
$K_{1,1}$	$\int_I E_I N_1'^2 dv + \int_{II} E_{II} N_1'^2 dv \quad (1)$	same
$K_{1,4}$	$\int_I E_I N_1' N_2' dv + \int_{II} E_{II} N_1' N_2' dv \quad (1)$	$\int_I E_I N_1' N_2' dv \quad (1)$
$K_{1,10}$	0	$\int_{II} E_{II} N_1' N_2' dv \quad (1)$
$K_{2,2}$	$\int_I G_I N_1'^2 dv + \int_{II} G_{II} N_1'^2 dv \quad (1)$	same
$K_{2,3}$	$\int_I G_I N_1' N_1 dv + \int_{II} G_{II} N_1' N_1 dv \quad (1)$	same
$K_{2,5}$	$\int_I G_I N_1' N_2' dv + \int_{II} G_{II} N_1' N_2' dv \quad (1)$	same
$K_{2,6}$	$\int_I G_I N_1' N_2 dv + \int_{II} G_{II} N_1' N_2 dv \quad (1)$	same
$K_{3,3}$	$\int_I (E_I S_I^2 N_1'^2 + G_I N_1'^2) dv + \int_{II} (E_{II} S_{II}^2 N_1'^2 + G_{II} N_1'^2) dv \quad (1)$	same
$K_{3,5}$	$\int_I G_I N_1' N_2' dv + \int_{II} G_{II} N_1' N_2' dv \quad (1)$	same
$K_{3,6}$	$\int_I (G_I N_1' N_2 + E_I S_I^2 N_1' N_2) dv + \int_{II} (G_{II} N_1' N_2 + E_{II} S_{II}^2 N_1' N_2) dv \quad (1)$	$\int_I (G_I N_1' N_2 + E_I S_I^2 N_1' N_2) dv \quad (1)$
$K_{4,4}$	$\int_I E_I N_2'^2 dv + \int_{II} E_{II} N_2'^2 dv \quad (1) + \int_I E_I N_1'^2 dv + \int_{II} E_{II} N_1'^2 dv \quad (2)$	$\int_I E_I N_2'^2 dv \quad (1) + \int_I E_I N_1'^2 dv \quad (2)$
$K_{5,5}$	$\int_I G_I N_2'^2 dv + \int_{II} G_{II} N_2'^2 dv \quad (1) + \int_I G_I N_1'^2 dv + \int_{II} G_{II} N_1'^2 dv \quad (2)$	same
$K_{5,6}$	$\int_I G_I N_2' N_2 dv + \int_{II} G_{II} N_2' N_2 dv \quad (1) + \int_I G_I N_1' N_1 dv + \int_{II} G_{II} N_1' N_1 dv \quad (2)$	same
$K_{6,6}$	$\int_I (E_I S_I^2 N_2'^2 + G_I N_2'^2) dv + \int_{II} (E_{II} S_{II}^2 N_2'^2 + G_{II} N_2'^2) dv \quad (1) +$ $+ \int_I (E_I S_I^2 N_1'^2 + G_I N_1'^2) dv + \int_{II} (E_{II} S_{II}^2 N_1'^2 + G_{II} N_1'^2) dv \quad (2)$	$\int_I (E_I S_I^2 N_2'^2 + G_I N_2'^2) dv + \int_{II} G_{II} N_2'^2 dv \quad (1) +$ $+ \int_I (E_I S_I^2 N_1'^2 + G_I N_1'^2) dv + \int_{II} G_{II} N_1'^2 dv \quad (2)$
$K_{10,10}$	0	$\int_{II} E_{II} N_2' dv \quad (1) + \int_{II} E_{II} N_1'^2 dv \quad (2)$

Table 2 - Timoshenko formulation: some terms of the stiffness matrix (I layer, 1 joint, (1) element)

