

# Examination of weld-seams

Autor(en): **Roš, M.**

Objektyp: **Article**

Zeitschrift: **IABSE congress report = Rapport du congrès AIPC = IVBH  
Kongressbericht**

Band (Jahr): **2 (1936)**

PDF erstellt am: **11.07.2024**

Persistenter Link: <https://doi.org/10.5169/seals-3295>

## **Nutzungsbedingungen**

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

## **Haftungsausschluss**

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.

## IIIc 6

### Examination of weld-seams.

### Prüfung der Schweißnähte.

### Essai et contrôle des cordons de soudure.

Dr. Ing. h. c. M. Roš,

Professeur à l'École Polytechnique Fédérale et Président de la Direction du Laboratoire Fédéral d'Essai des Matériaux et Institut de Recherches pour l'Industrie, le Génie Civil et les Arts et Métiers, Zurich.

The examination includes:

- 1) Weld-rods (Electrodes),
- 2) Welders,
- 3) Welding-seams in the finished structure.




Fig. 1.




Fig. 2.




Fig. 3.

Correct and incorrect closure of place whence specimen has been removed, by welding.

1) *Weld-rods (Electrodes)*. The melted weld-material is tested as regards strength, deformation-properties and sensibility with respect to quenching.

Test-piece taken from weld: — Weld material —

*Required values:*

Brinell-hardness  $H = 115$  to  $160$

Tensile-strength for steel as normally used in construction

( $\beta_z = 36 - 44$  kg/mm<sup>2</sup>,  $C \leq 0,15$  %):  $\beta_z = 40 - 55$  kg/mm<sup>2</sup>,

elongation after rupture  $\lambda_{10} = 15 - 25$  %.

Welding-“cords” laid down in thin layers — Sensibility with respect to quenching —

Flexure numeral:  $K = 50 \cdot \frac{S}{r} = 32 - 48$ .






Fig. 4.

Microscopic crack in structure of weld metal, not detectable by x-rays.

*Not compelling values:*

Yield-point  $\delta_s = 25 - 35$  kg/mm<sup>2</sup>

notch-tenacity of small normalised test-pieces EMPA  $x \geq 4$  mkg/cm<sup>2</sup>.

For high-grade steels separate agreements.

2) *Welder. — Workshop.* Plates and bars, of very small and large thickness as used in construction, welded in form of butt- and cruciform joints in normal as well as overhead position were examined by means of X-rays and afterwards subjected to the following tests: coarse-(macro) and fine-(micro)-structure, hardness, tensile-strength, folding-flexure capacity, repeated stress-strength and — by way of exception — to notch — tenacity. The selection of the test-pieces is carried out according to the results of the X-ray examination.

Failures of bond are not admissible. The structure must be free from cracks. For steel as normally used in construction the following is required: Hardness numbers of cross-section  $H = 115 - 160 \text{ kg/mm}^2$ , surface  $H \leq 180 \text{ kg/mm}^2$ ; tensile-strength — butt-joint — equal to that of the steel,  $\beta_z = 36 - 44 \text{ kg/mm}^2$ , tensile-strength — cruciform — joint average value  $\beta_z = 25 \text{ kg/mm}^2$ , minimum  $22,5 \text{ kg/mm}^2$ ; folding-flexure capacity  $K = 20 - 28$  (plate thickness  $\delta < 12 \text{ mm}$ ),  $K = 16 - 20$  ( $\delta = 12 - 20 \text{ mm}$ ) and  $K = 12 - 16$  ( $\delta > 20 \text{ mm}$ );

Repeated stress-strength — blunt-joint —  $\sigma_U \geq 15 \text{ kg/mm}^2$  — normal position —  
 $\sigma_U \geq 12 \text{ kg/mm}^2$  — overhead —

Repeated stress-strength — cross-joint  $\sigma_U \geq 6 \text{ kg/mm}^2$ .

For high-grade and special-steels, requirements ad hoc.

3) *Welding-seams. — Finished structure.* Discs or bars of suitable shapes (round, oval), are be taken from the finished structure or structural element at suitable points and tested in a similar manner, to comply with the same requirements as regards strength and deformation, as described in the preceding paragraph under „welders“. The characteristic values obtained must be within the same limits; only very slight differences are admissible. The places from which the test-pieces are taken must be made good with particular care to avoid accumulations of weld-metal and to minimise internal and shrinkage stresses (Fig. 3).

X-ray examinations serve to disclose nonconnected spots, pores, slag inclusions and cracks, but they do not reveal the presence of very fine hair cracks which are often undesirable — Fig. 4. Frequently the X-ray examination must be carried out twice, firstly on the weld-seams after completion of the welding, secondly after removal (by shaping, grinding, cutting) of the unevenness of the top-layers. This applies also to places whence test pieces have been removed.