

# Locating rebar corrosion in concrete walls by potential measurements

Autor(en): **Marquardt, Helmut**

Objektyp: **Article**

Zeitschrift: **IABSE reports = Rapports AIPC = IVBH Berichte**

Band (Jahr): **77 (1998)**

PDF erstellt am: **08.07.2024**

Persistenter Link: <https://doi.org/10.5169/seals-58183>

## **Nutzungsbedingungen**

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

## **Haftungsausschluss**

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.



## Locating Rebar Corrosion in Concrete Walls by Potential Measurements

**Helmut MARQUARDT**  
Prof. Dr.-Ing.  
FH Nordostniedersachsen  
Buxtehude, Germany



Helmut Marquardt, born 1956, received his civil engineering degree and doctor's degree from the Technical University of Berlin, 1983 and 1990 respectively. Since 1993, he is Professor in Buxtehude near Hamburg

### Summary

To localize corroding reinforcement in concrete buildings visual or sonic tests are not sufficient, because beginning corrosion cannot be recognized by these methods. By that means it is very likely that some areas starting to corrode will be missed - after a realized repair later damages may result. Therefore it is more useful to determine corrosion areas by electrochemical potential measurements.

Some application limits of the method of potential measurement have been examined. A special equipment has been developed to assess corrosion zones on the surfaces of concrete buildings.

### 1. Application Limits of Potential Measurements on Concrete Walls

The well-known method of potential mapping of bridges (fig. 1) is not transferable to concrete walls of buildings without problems, because the temperature and moisture of concrete walls is changing in a wide range, the concrete covering differs widely, concrete walls usually are surface finished by coatings or tiles, and often components of galvanized steel are used in concrete walls. Therefore the influences of the following parameters on the potential measurements have been examined:

- temperature and moisture of the concrete,
- thickness of the concrete covering,
- concrete surfaces with or without paints or coatings (fig. 2 and 3),
- components of zinc galvanized steel in concrete.

It could be shown that potential measurements do not depend on the temperature of the concrete but they were only possible between 30 and 90 % relative humidity of the surrounding atmosphere. Thick concrete coverings make it difficult to find small corrosion areas; fair-faced concrete walls coated e.g. with a thin acrylic paint are no problem (fig. 2), but on concrete surfaces with exposed aggregates by washing it is difficult to contact the cement grout (fig. 3). The interpretation of potential measurements in concrete walls with components of zinc galvanized steel is very difficult or impossible.

### 2. Measuring Equipment and Practical in-situ Tests

Coming from one half cell (cp. fig. 1) a more practical measuring equipment was developed: 6 CSE half cells were assembled in a frame, this enabled only one person to handle the equipment (fig. 4).

### 3. Conclusions

The reliability of the potential measurement method could be confirmed successfully by practical use on concrete walls.




Fig. 1 Scheme for potential measurements with a half cell on the surface of a reinforced concrete member




Fig. 4 View of the developed frame with 6 CSE half cells




Fig. 2 Dependence of the potential  $U_{CSE}$  on the distance  $x$  to the NaCl filled drill hole for different paints or coatings on the concrete surface




Fig. 3 Dependence of the potential  $U_{CSE}$  on the distance  $x$  to the NaCl filled drill hole for different lightweight concretes with or without thin acrylic paint