

Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte
Band: 79 (1998)

Artikel: Retrofit of corroded splice plates using epoxy glued escort plates
Autor: Sugie, Isao
DOI: <https://doi.org/10.5169/seals-59895>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. [Siehe Rechtliche Hinweise.](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. [Voir Informations légales.](#)

Terms of use


The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. [See Legal notice.](#)

Download PDF: 29.04.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

Retrofit of Corroded Splice Plates Using Epoxy Glued Escort Plates

Isao SUGIE
Civil Eng.
Hanshin Expressway Public Corp.
Osaka, Japan



Isao Sugie, born 1962, received his Civil Engineering degree from Kobe Univ. in 1985 and MSc in 1987. He is currently chief engineer of the Maintenance division of HEPC.

Summary

Corrosion can be the most serious problem, in particular, for very complicated steel structures such as truss bridges. The Port Bridge in Osaka suffered water leakage and then serious corrosion at the joints of the cross beams, which are also floor beams for the deck plates, between the main truss members. As a result, the head of bolts seriously corroded and the splice plates became 3 to 5 mm thinner than the original. For the retrofit, additional reinforcing plates (escort plates) glued with epoxy resin was chosen. The effectiveness of this method was researched in laboratory tests.

1. Outline of corrosion

The Port Bridge is the third longest Gerber truss bridge in the world. It was constructed in 1975 and connected the reclaimed lands of Osaka Bay area with a 450 metre centre span as shown in fig.1.

As shown in fig.2, rain water entered from the scallops of the web plate of cross beam welded to the main truss members. There are no drainage holes around them, and the box beams have collected water inside them. As a result, corrosion has been advanced at the lower flange joints of the cross beams. This created two structural problems. One is the reduction of axle force of the high tension bolts. The maximum rate of measured reduction was 30 %, which is bigger than that due to relaxation (approximately 10 to 15%). Another is the reduction of thickness of the splice plates. The most corroded one was 5 mm thinner than the original. Finally, the stress limitation can not be guaranteed at the joints.




Fig.1 Overall-view of the Port Bridge




Fig. 2
General view
around corroded
joint

2. Retrofit concept

Fig.3 shows the retrofit using epoxy glued escort plates. In this method, the original splice plate can remain and only a row of bolts can be removed. These are replaced with new ones at the same time for fitting a long rectangular escort plate. The bolts should be replaced from the centre to the corners of the flange, so that re-distribution of the stress flow can be improved. Filler plates should be also fitted to make up for the lack of thickness of the corroded flange plates. Other methods for retrofit have been considered such as replacement of the whole splice plates or reinforcing them with additional plates fixed by welding. They, however, were rejected for the following reasons.

(1) The working stresses due to dead loads are too large to remove the whole splice plate and all bolts from the lower flange at the same time.

(2) The influence of welding would be great, because high tension steel (HT70, HT80) was used. Finally, using epoxy glued escort plates resulted in the most effective and practical method.

Laboratory tests have been done to examine the effectiveness of this method. The two bolts model test indicated that there were no remarkable difference between the sound specimen and the corroded ones reinforced by the escort plate.

It should be noted that using epoxy resin together with H.T.bolts may be able to reduce the number of bolts at the design stage.




Fig. 3
Retrofit of
corroded splice
plates using
epoxy glued
escort plate