

Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte
Band: 83 (1999)

Artikel: FRP reinforcement for concrete structures: state-of-the-art
Autor: Taerwe, Luc / Matthys, Stijn
DOI: <https://doi.org/10.5169/seals-62878>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 16.07.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>



FRP Reinforcement for Concrete Structures : State-of-the-Art

Luc TAERWE

Professor
University of Ghent
Ghent, Belgium

Luc Taerwe, born 1952, graduated in 1975 at the University of Ghent as civil engineer where he also obtained his doctor's degree. Actually professor of structural concrete. Recipient of RILEM's Robert L'Hermite Medal and the IABSE Prize. Member of the fib Council and Steering Group and convenor of fib Task Group 9.3 'FRP reinforcement'

Stijn MATTHYS

Civil Engineer
University of Ghent
Ghent, Belgium

Stijn Matthys, born 1969, graduated in 1991 as industrial engineer and in 1994 as civil engineer. Since then, he is a doctoral researcher at the Magnel Laboratory, specialised in 'design recommendations for FRP reinforcement'.

Summary

Several types of FRP (fibre reinforced polymers) reinforcement have been developed in recent years. These elements are not susceptible to the usual types of corrosion. The paper gives a survey of the main characteristics of FRP reinforcement and shows some of the applications.

Keywords: Fibre Reinforced Polymers, FRP reinforcement, concrete, state-of-the-art

1. Introduction

If properly designed, constructed and maintained, reinforced or prestressed concrete structures generally have service lives of 50 years and more. Nevertheless, durability problems often occur, among which corrosion of steel, especially for concrete structures in aggressive environments. Hence, there is an increasing interest in the use of non-metallic reinforcement which is not susceptible to the classical types of corrosion. Recent evolutions in the field of material engineering offer new possibilities, such as the use of advanced composites or "fibre reinforced polymers". These so-called FRP reinforcements can serve as a viable alternative to reinforcing and prestressing steel, as has been demonstrated by several research and demonstration projects.

2. Materials

As structural reinforcement for concrete members, FRP elements are made available in the form of bars, tendons, ropes, grids, sheets or profiles. For new structures, they are used to reinforce and prestress concrete elements. In the repair sector, they are used to strengthen existing structures e.g. by means of external post-tensioning, external sheet bonding or in combination with shotcrete. The tensile stress-strain behaviour of FRP made of aramid, carbon and glass fibre (AFRP, CFRP and GFRP) as compared to reinforcing and prestressing steel are shown in figure 1. Similar to the behaviour of the fibres and unlike steel, FRP do not experience any yield but rather a linear elastic




Fig. 1. Stress-strain curves of FRP elements

3. State-of-the-Art Overview

When FRP is used for reinforced concrete (RC), the low modulus of elasticity results in large deformations. This makes FRP (from a structural point of view) more suitable for prestressed concrete (PC). Nevertheless, a number of projects with FRP RC members have been completed. Concerning pre- and post-tensioning with FRP, several applications are available in Japan, Europe and North-America.

Whereas, the application of structural FRP reinforcement for RC and PC members basically concerns demonstration projects so far, the use of externally bonded FRP reinforcement is growing commercially in a fast way. With this strengthening technique both advanced properties and ease-of-application are offered.

4. Design Guidelines

The considerable interest in FRP as structural reinforcement will only successfully result in applications on a broader basis, if design guidance and finally code regulations are available. In Japan, the U.S.A., Canada and Europe several initiatives have been. A fib (International Concrete Federation) Task Group "FRP Reinforcement", convened by the first author, is elaborating design recommendations based on the design format of the CEB-FIP Model Code and Eurocode 2.

5. Conclusions

FRP reinforcement may offer a practical and economical alternative to conventional steel reinforcement. It must be appreciated that the application of FRP reinforcement is partly in an experimental stage and that different aspects of this new technology will be the subject of more detailed investigations. Nevertheless, several initiative to establish design guidelines have been taken as a result of the considerable interest in this novel reinforcing material.

The application of FRP reinforcement is related to the utilisation of the specific material properties of FRP. Therefore, it has to be used as a specific alternative for common steel reinforcement, rather than a general substitute for it.

behaviour nearly up to failure. Compared to steel, the Young's modulus for FRP is often much less and ranges between 50 to 250 GPa, while the tensile strength is close to that of prestressing steel. The mechanical properties of aligned composite materials transverse to the fibres are much less than those parallel to the fibres.