

Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte
Band: 83 (1999)

Artikel: Stress-based crack criterion for concrete at early ages
Autor: Van Breugel, Klaas / Lokhorst, Sander J.
DOI: <https://doi.org/10.5169/seals-62889>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. [Siehe Rechtliche Hinweise.](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. [Voir Informations légales.](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. [See Legal notice.](#)

Download PDF: 22.12.2024

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>



Stress-Based Crack Criterion for Concrete at Early Ages

Klaas VAN BREUGEL
Senior Lecturer
Delft University of Technology
Delft, The Netherlands

Klaas van Breugel, born 1952, received his civil engineering degree from Delft University of Technology in 1979 and his doctor degree from the same university in 1991.

Sander J. LOKHORST
Civil Engineer
Holland Rail Consult Utrecht
Utrecht, The Netherlands

Sander Lokhorst, born 1967, received his master degree at Delft University of Technology in 1992. He was employed at TU-Delft until 1997 and since then in a consulting company in Utrecht, The Netherlands.

Summary

In order to enhance the quality of concrete structures, cracking in hardening concrete should be prevented as far as possible. A traditional way to assess the risk of cracking at early ages consists of minimising temperature differentials between warm and cold concrete. In this contribution the results of a recently finished study on the risk of cracking and crack criteria of hardening concrete are presented. The stress development and the tensile stress at the moment of cracking have been measured in a Temperature Stress Testing Machine. Based on the test results a criterion for cracking at early ages is formulated. A procedure for determination stresses in hardening concrete is briefly discussed. In this procedure allowance is made for the effect of the evolution of the microstructure on relaxation of stresses at early ages.

Keywords: Hydration; thermal stresses; cracking; creep; relaxation; modelling; crack criteria

1. Introduction

In the engineering practice the risk of cracking in hardening concrete has often been formulated in terms of allowable temperature differentials. From observations in the practice as well as from theoretical considerations it has become clear that temperature criteria are very crude. The actual risk of cracking can be overestimated and underestimated considerably, resulting in too conservative or too optimistic designs. Strain or stress criteria are considered more appropriate. In this contribution both experimental and mathematical studies concerning stresses and the risk of cracking in young concrete are dealt with. The aim is to define a stress criterion for cracking of hardening concrete.

2. Outline of research strategy

For the prediction of the risk of cracking in hardening concrete the evolution of the materials properties with elapse of time must be known. In this study the development of materials properties is described as a function of the degree of hydration. The correlation between degree of hydration and strength has been demonstrated many times. More recently also attempts have been made to describe the time-dependent properties of hardening concrete as a function of the degree of hydration. This strategy has also been followed in the theoretical part of this research project. In the experimental part of the project the development of thermal stresses in hardening concrete has been investigated with a Temperature Stress Testing Machine.

3. Determination of stress development and cracking of hardening concrete

The development of stresses in hardening concrete and the risk of cracking was investigated experimentally for a number of different concretes with a Temperature-Stress Testing Machine (TSTM). With this machine stress development due to restrained deformations as well as creep and relaxation behaviour under prescribed thermal conditions were investigated. The mixtures were made with Portland cement and blast furnace slag cement and with water/cement ratios varying from 0.3 to 0.6. Curing of the concrete took place either isothermally or semi-adiabatically. Imposed deformations were restrained in whole or in part.

4. Crack criterion for young concrete and prediction of tensile stresses

For all the concrete specimens considered in the experimental program self-induced cracking occur-red at an average stress/strength ratio 0.75. Based on this data a probabilistic judgement concept is proposed in the form of a nomogram (Fig. 1). The nomogram is based on the assumption of a normal distribution of both the tensile strength and tensile stresses. With the graph an allowable stress/strength ratio η can be determined for each pre-defined probability of cracking which is considered appropriate for the concrete structure in view. This allowable stress/strength level η can be compared with the development of the stress and the strength obtained by simulation.

For prediction of the tensile stresses at early ages a calculation procedure is proposed in which allowance is made for some microstructural phenomena which occur in hardening concrete. Examples of stress predictions are presented. Preliminary results obtained with this microstructure-based calculation procedure are encouraging.




Fig. 1 Design graph for the determination of the maximum allowable stress/strength ratio in a hardening concrete structure