

Chemical and isotopic characterization and production technique of subferrate asses of the Lyons Altar series (part 1)

Autor(en): **Klein, Sabine / Kaenel, Hans-Markus von**

Objektyp: **Article**

Zeitschrift: **Schweizer Münzblätter = Gazette numismatique suisse = Gazzetta numismatica svizzera**

Band (Jahr): **70 (2020)**

Heft 277

PDF erstellt am: **30.06.2024**

Persistenter Link: <https://doi.org/10.5169/seals-867834>

Nutzungsbedingungen

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

Haftungsausschluss

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.

Chemical and isotopic characterization and production technique of subferrate asses of the Lyons Altar series

Sabine Klein,
Hans-Markus
von Kaenel

The early Roman Imperial *AES* Coinage IV.

Content

Part I

1. The find spot and the coin ensemble	4
2. Subferrate Lyons Altar <i>asses</i>	4
3. Description and documentation of the examined coins from Gross-Rohrheim from a metallurgical point of view	8
3.1. The coins	8
3.2. The iron flan	10
3.3. The copper layer	12
Acknowledgements	15
References Part I	17

Part II (to be published in June 2020 in the next fascicle «No. 278»)

4. Analytical data and their discussion	
4.1. Chemical analysis	
4.2. Lead isotope analysis and provenance of the copper metal used for the plating	
5. Production technique of coin 4	
5.1. Different techniques for the production of plated coins	
5.2. Experimentally produced copper plating on iron flans by M. Pfisterer and R. Traum	
5.3. Arguments for the application technique of sheet copper for coin 4	
5.4. Numismatic conclusions	
References Part II	

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate *asses* of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

1. The find spot and the coin ensemble

A few years ago we conducted a study on the chemical composition and isotope ratios of copper coins of Augustus from the mint of Lyons/Lugdunum¹. As a supplement we present in the following four *asses* from Gross-Rohrheim (Bergstrasse district, Hesse state, Germany), which are typologically attributable to this group and which do not consist of solid copper but of an iron core surrounded by a copper skin (*Fig. 1–5*). Due to the conditions of the soil, the iron core of three of the four coins is strongly corroded, has formed bubbles in the copper shell and has blown them up in individual places (*Fig. 1.3–5*). The four coins were discovered within the framework of systematic field surveys agreed with the Landesamt für Denkmalpflege Hessen – hessenArchäologie, Aussenstelle Darmstadt, and are part of a remarkable new ensemble of Roman finds from the right bank of the Rhine, which will be presented elsewhere² and discussed in the context of the early Roman finds from southern Hesse³.

The four subferrate Lyons Altar *asses* are part of an important early imperial ensemble comprising around 160 coins, which consists of Roman Republic *asses*, coins of the Augustan moneyers series and from Nîmes/Nemausus as well as *asses* and *semisses* of the Lyons Altar series⁴. The series of 19 silver coins ends with six denarii for Caius and Lucius Caesares as *principes iuventutis*⁵ minted around the birth of Christ. Silver from the reign of Tiberius is missing. The most recent coins are two Tiberian *asses* of the DIVVS AVGVSTVS PATER series⁶, one of the type RIC I² 72 (circa 15/16 AD) and another of the type RIC I² 81 (probably early, middle, and late Tiberian). The represented countermarks fit well into the type repertoire of the late Augustan/early Tiberian countermarks on the Upper Rhine⁷.

Thanks to the finder's, J. Lotter, courtesy, one of the four *asses* (No. 4) could be divided into two parts (*Fig. 4.5*) for the purpose of a detailed technological and analytical investigation. We are therefore in a position to precisely document and describe the coin in question, to reconstruct its manufacture and to characterise the metals geochemically. In addition, the isotope ratios for the copper used are determined and discussed.

2. Subferrate Lyons Altar *asses*

The adjective subferrate (*nummus subferratus*) represents a modern word creation⁸ formed according to the Latin term (*nummus*) *subaeratus*⁹. If the core cannot or should not be differentiated, one generally speaks of “plated coins”. Subaerate coins in the form of republican and imperial *denarii* and *quinarii* as well as Gallic silver coins are common. An overview of more than 3500 Late Latène, Republican and Augustan/Tiberian silver coins from 20 significant sites in northern Gaul and the Rhine areas, compiled by the author, shows that about 75 % of them consist of solid silver, while about 25 % are clad silver coins. For 377 silver coins from the reigns of Augustus and Tiberius the ratio is 65 % : 35 %. Among the individual finds from the Roman colony of *Augusta Raurica*, 104 (32 %)¹⁰ of the 326 silver coins are subaerate. The mass of the cores consists of

- 1 KLEIN et al. 2012; the other contributions: KLEIN et al. 2004; KLEIN – VON KAENEL 2000.
- 2 M. HELFERT – H.-M. VON KAENEL – J. LOTTER (in preparation); for a republican denarius from the find spot with graffiti see KEMMERS – SCHOLZ 2017.
- 3 MAURER 2011.
- 4 The quantitative ratio between the coins of the Altar series I : II is about 1 : 2.
- 5 WERZ 2018a; WOYTEK – BLET-LEMARQUAND 2017; WOLTERS 2002; for the distribution of the type WOLTERS 2017, pp. 48–55; BERGER 1996, pp. 25–31.70–73 (lists).
- 6 For the dates of the two types see BARRANDON et al. 2010 and KLEIN – VON KAENEL 2000, pp. 75–79.
- 7 On the current state of discussion, which is controversial in many respects, see MARTIN 2018; WERZ 2018b; WIGG-WOLF 2018; WOLTERS 2018.
- 8 *Sub* (beneath) *ferrum* (iron).
- 9 *Sub* (beneath) *aes* (copper, bronze); documented in Persius, Satires V, 106.
- 10 PETER 2004, p. 21, note 9.

copper, iron cores are comparatively rare. The production of plated coins was not limited to the Roman and Gallic minting, rather there are already corresponding Greek coins¹¹.

The question of how plated silver coins are to be legally judged has long been the subject of controversy; a consensus has emerged, though not universal, in favour of interpreting such coins as counterfeit money¹². However, the one-sided discussion from the point of view of Roman law has greatly narrowed the view of the complexity of this remarkable phenomenon. Plated coins were widespread and a reality also outside the sphere of Roman law. Which practices were developed locally in dealing with plated coins – and which negotiation processes took place to define value and equivalence in connection with the acceptance and distribution of these coins – are at least as interesting aspects as the legal assessment “genuine” or “false”¹³. Against this background, the considerations of M. Pfisterer¹⁴, differentiated in terms of content and terminology, on the interpretation of subferrate *aes* and cast coins are helpful.

After a series of pioneering works¹⁵ on the *nummi subferrati*, important contributions to the subferrate coinages from the late 2nd and first decades of the 3rd century AD in Noricum and Pannonia¹⁶ recently appeared. In this context, the production technique of subferrate coins¹⁷ also received due attention. In 2017, an international team of authors led by J.-M. Doyen, St. Martin and M. Peter presented the first systematic and comprehensive study¹⁸ on subferrate *aes* coinages of the Roman Imperial Period. On the basis of a compilation of nearly 1800 corresponding coins from the four Gallic, the two Germanic provinces as well as *Raetia*, the *Alpes Poeninae*, *Noricum* and *Pannonia*, the study provides a systematic geographical, chronological and typological overview of the different groups of subferrate copper and brass coins. At the current state of knowledge¹⁹, however, subferrate coins appear to be very rare in Italy, the Spanish provinces and Britain.

The practice of minting Lyons Altar coins by surrounding an iron core with a thin copper skin is part of a larger context. As the systematic study clearly shows, in the Julio-Claudian period in Gaul and on the Rhine subferrate *aes* coins imitating coin types of Augustus, Tiberius, Claudius and Nero occur, whereby those after Augustan types obviously make up the majority²⁰. These also show the widest distribution in Gaul and on the Rhine, whereas subferrate *aes* coins based on types of Tiberius, Claudius and Nero seem to concentrate rather on the Lower Rhine. But even after that period, subferrate coins were still produced in this area until the end of the 2nd century. In the course of the second half of the 2nd century the production of subferrate and cast coins began in the middle Danube basin²¹. Parallel to the subferrate *aes* coins of types of the Julio-Claudian emperors, masses of imitations²² in copper, more rarely in brass, which were of poor manufacture and style and heavily underweighted, circulated in Gaul and on the Rhine.

The subferrate specimens representing the Lyons Altar series I and II²³ are usually *asses*, rarely *semisses* (series II). In the repertory of the comprehensive study, a total of 90 corresponding coins²⁴ are listed for the territory of the present Netherlands (5), Belgium (4), France (36), Luxembourg (23), Germany (11) and Switzerland (11). They account for about 75 % of the 120 subferrate coins

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate *asses* of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

- 11 OLSEN et al. 2020; VAN ALFEN 2005; MOESTA – FRANKE 1995, pp. 35–36.106–109.
- 12 CRAWFORD 1968; RRC pp. 560–565; CRAWFORD 1985, pp. 187–191; PETER 2011; PETER 2004; problematic, however DEBERNARDI 2010.
- 13 Important for the relevant written sources and their discussion PFISTERER 2007b, pp. 765–768.
- 14 PFISTERER 2007a, p. 642; PFISTERER 2007b, pp. 768–772.
- 15 DEMBSKI 1993; ZEDELIOUS 1988; ZWICKER – DEMBSKI 1988; VAN HEESCH 1987; THIRION 1975.
- 16 PINTZ 2014; PFISTERER 2007a; PFISTERER 2007b; PFISTERER 2006.
- 17 HAUBNER et al. 2016; PFISTERER 2007b; PFISTERER – TRAUM 2005a; PFISTERER – TRAUM 2005b; ZWICKER – DEMBSKI 1988.
- 18 DOYEN et al. 2017.
- 19 DOYEN et al. 2017, pp. 207–208 with map 1.
- 20 DOYEN et al. 2017, p. 217 Fig. 8.
- 21 DOYEN et al. 2017, pp. 229–232 with maps 6–13.
- 22 MARTIN 2015, pp. 294–312; NUSSE 2014; DOYEN 2007, pp. 120–124; WIGG-WOLF 2004; WIGG-WOLF 1996, pp. 424–436; GIARD 1970.
- 23 Altar series I, ca. 7–3 BC (RIC I² 230; VAN HEESCH 1993); Altar series II, ca. 8 (?)/9–14 AD (RIC I² 233. 237. 238. 242. 245). – On the numismatic and historical classification of the two coin types KLEIN et al. 2012, pp. 65–72; DOYEN 2007, pp. 51–62; GIARD 1983.
- 24 DOYEN et al. 2017, pp. 227 (map 2).280–294 (lists).

S. Klein, H.-M. von Kaenel: Chemical and isotopic characterization and production technique of subferrate *asses* of the Lyons Altar series, SM 70, 2020, S. 3–21.

by coin types from the reign of Augustus. In addition to subferrate Lyons Altar coins, subferrate specimens from Nîmes/Nemausus and – rarely – moneyers *asses*²⁵ also occur. The authors of the study rightly assume that a considerable number of unreported subferrate coins is to be expected because they were not recognizable as such in view of their generally poor state of preservation²⁶. On account of the magnetism of the iron core, a magnet however would easily indicate the special manufacture of these coins²⁷. Unfortunately, the lists of the systematic study as a whole do not contain any information on the style and manufacture of the subferrate coins; if one consults original publications²⁸ with illustrations, then it becomes apparent that the subferrate Lyons Altar coins are not exclusively, but often imitations (*Fig. 3*).

As a comparison with the distribution map of the *asses* of the Lyons Altar series I²⁹ in Gaul and on the Rhine compiled by F. Berger shows, the occurrence of subferrate specimens of the series I is precisely classified in this category. The coins in question are found not only in military camps, but also in civil settlements and sanctuaries. In quantitative terms, however, they seem to have played a marginal role. The Augustan period ensemble from the sanctuary of La Ville-neuve-au-Châtelot (Aube) consists of 1282 Celtic and Roman coins, including 558 *asses* from the Lyons Altar series I with a total of seven (1.2 %) subferrate specimens³⁰. Five (1.0 %) of the 477 corresponding coins from the Colony of Augusta Raurica³¹ are subferrate. The fantastic quantities of subferrate coins postulated by a co-author of the comprehensive study are therefore to be regarded as implausible: “*Dès lors, c’est sans doute par dizaines de millions, voire par centaines de millions qu’il faut estimer la production globale des subferrati*”³².

As far as the date of production of subferrate *aes* coins is concerned, the study distinguishes between two chronologically and territorially clearly separated phases, a first in the early imperial period (20/30–60/70 AD) and a second in the second half of the 2nd and the first of the 3rd century AD (around 160–260 AD)³³. In the first phase, which mainly affects Gaul and the Rhineland, subferrate *asses* (copper/iron) dominate, in the second (Noricum, Pannonia) subferrate brass coins (brass/iron)³⁴.

For the subferrate Lyons Altar coins, the above-mentioned chronological approach, the justification for which is not very convincing, remains to be specified. One of the arguments for the beginning of the production of such coins during the reign of Augustus is the following: The ensemble of La Ville-neuve-au-Châtelot, found in 1973 was, as it turned out after its discovery, part of a Gallo-Roman sanctuary, which was subsequently excavated. The coin series consists of 32 silver wheels, 66 Gaulish and 1184 Roman coins; the most recent coins³⁵ are 558 *asses* of the Lyons Altar series I and 225 coins from Nîmes/Nemausus of the type RPC I 524. The countermarks represented on the coins in the ensemble of La Villeneuve-au-Châtelot are part of a late Augustan horizon with, among others, ten VARVS countermarks³⁶. Since there are no countermarks that can be clearly identified as Tiberian, there is much to suggest that the ensemble represents a part of ritual deposits from the late Augustan period. Among the 558 *asses* of the Lyons Altar series I a total of seven subferrate *asses*³⁷ are documented. The coin series from Gross-Rohrheim now also provides a

25 PETER 2001, p. 53 vs. DOYEN et al. 2017, p. 215.

26 DOYEN et al. 2017, pp. 208–209.211.

27 ZWICKER et al. 1993, p. 233.

28 *Augst*: all 5 subferrate Lyons *asses* are imitations: PETER 1996, pp. 161–162
Inv.-No.1958.11927 (series II). p. 233 Inv.-No. 1959.9348 (series I). Inv.-No. 1960.5429 (series I). p. 345, Inv.-No. 1968.5979 (series II). p. 353 Inv.-No. 1969.6292 (series II). – *Martberg*: 8 subferrate Lyons *asses*, from which 7 are imitations: FMRD IV 4,1, 4001, 1, No. 1205 (series I, regular). No. 1272 (series II, imit.). No. 1291 (series II, imit.). No. 1328–1331 (series I/II, imit.); FMRD IV, 4001, 6, No. 599 (series I/II, imit.). – *Xanten*: 1 subferrate *as*, imitation: KOMNICK 2015, p. 64 No. 631 (barb?).

29 BERGER 1996, Fig. 20.21.

30 ZEHACKER et al. 1984, pp. 61.77–84.

31 See note 28; DOYEN et al. 2017, p. 283–284; PETER 2001, pp. 53–54.

32 DOYEN et al. 2017, p. 226.

33 DOYEN et al. 2017, pp. 215–216.219–220.

34 DOYEN et al. 2017, pp. 243–280 (lists); PFISTERER 2007b.

35 ZEHACKER et al. 1984, pp. 41–44 No. 402–626 (Nîmes/Nemausus). pp. 45–54 No. 627–1184 (Lyons Altar series I).

36 ZEHACKER et al. 1984, pp. 77–84. – The governorship of Varus on the Rhine began in 7 AD and ended in the disaster of 9 AD.

37 See note 30.

chronologically important indication. They also suggest the production of subferrate Lyons Altar coins already in reign of Augustus in central/northern Gaul, including the Rhine basin. It is an area with a strong local tradition of minting coins in the Late Latène period. With the beginning of the difficult process of Romanization of the *Tres Galliae*³⁸ under Augustus, in which Roman structures were also enforced against resistance, the local minting activity did not disappear but changed. This is not only supported by “romanized” coin emissions such as RPC I 506³⁹, 508⁴⁰ and 509, but also “Gallic” ones such as the AVAVCIA bronzes⁴¹, as well as imitations and subferrate coins that differ from their manufacture, weight, style and design.

The reason for the local minting activity lay in the scarcity of small change caused by the gradual monetarization of the *Tres Galliae*⁴², to which the stationing of large contingents of troops on the Rhine much contributed. Although considerable quantities of regular copper coins were available, the official mints in the Julio-Claudian period – unlike for the precious metal – did not cover by far the demand for small coin units. This *laissez faire – laissez aller* policy left room for local minting activities for decades. Whoever stood behind the relevant workshops, individual personalities, communities, troops, “counterfeiters”, these coinages evaded a simple, generally binding categorization into “genuine” or “false” in practice. The Roman provincial authorities did not intervene because they did not suffer any damage as a result, but the financial administration determined the form in which taxes and duties were accepted (gold, silver coins, certain goods)⁴³; coins in copper were not one of them. Moreover, the individual taxpayer did not pay his taxes directly to the *fiscus*, but to the local authority to which he belonged, and it was this entity which paid the total amount of the tax fixed for it.

We know nothing about how the mass of imitations and also subferrate copper coins – as far as they were recognized as such – were dealt with in everyday life during the early imperial period in Gaul and on the Rhine. Since there is no evidence that attempts had been made to enforce “bad” small change at the official nominal value, it must have been left to local negotiation processes between the actors concerned to determine the value at which corresponding coins changed hands locally. The material value, metal and weight, will have represented the decisive criteria.

Altogether, the production of subferrate Lyons Altar coins documents a very revealing but quantitatively unimportant aspect in the complex and protracted process of monetarization of vast territories in the northwestern provinces of the Roman Empire.

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate *asses* of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

38 ARBABE 2017, pp. 103–169;
DONDIN-PAYRE 1999.

39 Type SCHEERS 1983, 216; DOYEN
2007, pp. 63–85.

40 See the remarkable number of
about 1500 coins of this type
from the source of Bourbonne-
les-Bains (Haute-Marne) in
SAUER 2005, pp. 18.248–276;
DOYEN 2007, pp. 90–93.

41 Type SCHEERS 1983, 217; AARTS
et al. 2009; in this context
important the deposit of about
100 coins of the type SCHEERS
1983, 217, see pp. 822–823. pl.
XXVI no. 746, with lead cores
and very thin copper skins
(*nummi subplumbati*); see
BURKHARDT 1989, p. 30; ILISCH
1999, pp. 285–286 and below
note 96.

42 DELESTRÉE 2017; MARTIN 2015,
pp. 177–250; MARTIN 2011; VAN
HEESCH 2009; VAN HEESCH 2005;
GIARD 1970.

43 For the collection of taxes
DE LIGT 2009; for the financial
matters see MARTIN 2015,
pp. 208–212.

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate *asses* of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

3. Description and documentation of the examined coins from Gross-Rohrheim from a metallurgical point of view

3.1. The coins

Series I (7–3 BC?)⁴⁴

Obv.: CAESAR PONT MAX. Laureate head of Augustus to the right.
Rev.: ROM ET AVG. Altar of Roma and Augustus at Lugdunum.
RIC I² 230

No. 1 (Fig. 1)

Found in 2009 by J. Lotter; Find No. 090 138. – 11.52 g; Diameter 2.66 cm.
Obv.: Above strong corroded marginal part, below burst bubble. Rev.: Strong corrosion in the marginal parts and in the centre.



Fig. 1: coin 1 (scale 1:1)

Series II (8 ?/9–14 AD)

Obv.: TI CAESAR AVGVST F IMPERAT V or VII. Laureate head of Tiberius to the right
Rev.: ROM ET AVG. Altar of Roma and Augustus at Lugdunum.
RIC I² 238a. 245.

No. 2 (Fig. 2)

Found in 2008 by J. Lotter; Find No. 081 213. – 10.31 g; Diameter 2.42 cm; Die axis: 240°.
Imitation; clumsy letters on the obv.
Obv.: Well preserved dark patina; under the bust and above the head of Tiberius the iron core becomes visible.



Fig. 2: coin 2 (scale 1:1)

⁴⁴ For the chronology of the two series see note 23.

Only available as photo:

No. 3 (*Fig. 3*)

Found by M. Paulsen.

Obv.: Identification secured by letter remains and the ribbons of the wreath; strong encrustation and traces of corrosion at the edges, burst bubble in front of the face of Tiberius. Rev.: Right part of the altar recognizable; strong encrustation and corrosion.



Fig. 3: coin 3 (scale 1:1)

Series I/ II

No. 4 (*Fig. 4*)

Found in 2008 by J. Lotter; Find No. 081 215. – 10.86 g; Diameter 2.68 cm.

Obv. and rev. decentered. Obv.: Head to the right, strong corrosion and burst blisters. Rev.: Strong corrosion and large bubble, partly cracked.

Cut into two parts for this research with the permission of the finder J. Lotter (*Fig. 5*).



Fig. 4: coin 4 (scale 1:1)



Fig. 5: coin 4 (scale 2:1). Left: cut in two halves; right: cut surfaces

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate *asses* of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

S. Klein, H.-M. von Kaenel: Chemical and isotopic characterization and production technique of subferrate *asses* of the Lyons Altar series, SM 70, 2020, S. 3–21.

To the best of our knowledge, no specimen of the early imperial group of subferrate *aes* coins of interest here has yet been analyzed and discussed with regard to its production process. On the other hand, important studies are available on the *aes* imitations with iron cores from the late 2nd and early 3rd centuries AD, but their occurrence is concentrated on the middle Danube in Austria⁴⁵. A number of contributions⁴⁶ have dealt with the metallurgy and production techniques of these coins.

The primary analytical investigation was carried out on composite coins⁴⁷ with the focus on Faustina II subferrate coins imitating corresponding *sestertii* and found at Enns and *Flavia Solva* in Austria. They discovered that the Enns coins were made of iron coated with a thin layer of Cu-Sn alloy (bronze), whereas the coins from *Flavia Solva* were coated with Cu-Zn (brass). From their modern appearance, the subferrate composition of the coins is obvious, as the original surfaces of the coins are inflated by iron corrosion. Earlier analytical and metallographic studies also showed a certain diversity in the production technique, which will be summarized later in this text.

The more complex composition and structure of the substrate coins requires detailed analytical and metallographic investigation, and valuable information cannot be obtained by non-destructive surface methods such as portable X-ray fluorescence spectrometry, minimally invasive portable laser ablation samples or surface leaching techniques, as these methods cannot penetrate into the rust-free core. This study examines and compares the subferrate coins of interest with an experimentally produced blank by R. Traum and M. Pfisterer, Vienna, using minimally invasive methods. In addition to the element and isotope analysis of the components, the focus here is on the microstructural identification of the composition of the iron core and copper layer as well as on technical aspects. The metallographic observation is limited to one (coin 4 – *Fig. 4*) of the four subferrate coins, which we were allowed to halve and thus study microstructural details. A polished profile was prepared for metallography. Coins 1 and 4 (*Fig. 1*, *Fig. 4*) were sampled by micro-drilling for the element and isotope composition, coin 3 was only available as a photo (*Fig. 3*).

Since the subferrate Lyons Altar as analyzed here was found in a completely different area and manufactured almost 200 years earlier than the *aes* coinages with iron core in the Danube basin, we first discuss our results from the point of view of the distribution area of the Lyons Altar series in Gaul and on the Rhine. Due to the lack of metal analytical investigations of subferrate *aes* coins from the early imperial period, we will also discuss the contributions dealing with the subferrate silver coins⁴⁸ of this time.

3.2. *The iron flan*

The iron flan has concave rounded (barrel-shaped) edges and is clearly consistent in the thickness of 2.1–2.05 mm. The slightly wavy surface (*Fig. 6*) on the peripheral surface of the iron flan is visible and is certainly caused by the impact of the iron flan prior to the coating process. Barrel-shaped edges occur when a steel rod is used and cut into slices. By flat hammering the slices, blanks of equal diameter can be produced⁴⁹.

45 See note 16.

46 See note 17.

47 ZWICKER–DEMBSKI 1988.

48 ANHEUSER 1998; ANHEUSER – NORTHOVER 1994; ZWICKER et al. 1993.

49 PFISTERER – TRAUM 2005a, p. 139 pl. 8; further description of their technique see PFISTERER – TRAUM 2005b.




Figure 6: Coin 4. Backscattered image (BSE), electron microprobe analysis: Wavy surface of the iron flan (left, BSE: grey) indicating the flattening process. Right in the image is the copper layer (BSE: white; coin is diagonally oriented). Upper right corner (black) is resin.

The metallographic examination of the halved subferrate coin 4 (*Fig. 5*) was performed on a polished section without and with etching using a polarized light microscope (Zeiss Axiophot). Already as polished it becomes visible that the iron flan of the subferrate coin was made of homogeneous ferrous metal. Deformation twins in the iron flan⁵⁰ (Neumann lines) are not present here. Etching with a 2 % nital solution, an oxidizing etchant of nitric acid in ethanol, is usually used for the formation of Fe-C microstructures and shows a ferrite-pearlite microstructure (*Fig. 7*), which consists of hypoeutectic iron and thus the carbon content is < 0.8 % C. Overheated areas are located at the edges of the flan (*Fig. 9*). Based on the microstructure of the coin, the carbon content of the iron flan is even more accurate at 0.4 % C. This composition is consistent with other studies investigating subferrate coins with different archaeological contexts, appearance and composition of the coating (copper, tin, zinc and lead – a “*buntes Gemisch*”⁵¹): Low-carbon steel⁵² (< 1 % C⁵³, 0.15 % C⁵⁴) is reported. The low carbon content and the slag inclusions (*Fig. 8*) indicate the use of bloomery iron for the production of the iron flan. The low carbon content of the iron is typical for the entire Roman Empire⁵⁵. An analysis is performed for an iron core in context of subaerate coinage consisting of wrought iron (99.8 % Fe, 0.07 % Ni, 0.06 % Sn) with a ferritic equiaxed grain structure⁵⁶.

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate asses of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

50 HAUBNER et al. 2016.

51 Colourful mix, see PINTZ 2014,
p. 218.

52 HAUBNER et al. 2016.

53 PINTZ 2014.

54 ZWICKER – DEMBSKI 1988.

55 PINTZ 2014.

56 ANHEUSER – NORTHOVER 1994,
p. 24 coin no. 5

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate *asses* of the Lyons
Altar series, SM 70, 2020,
S. 3–21.




Figure 7: Iron flange of coin 4 as etched with Nital. Hypo-eutectic structure comprises of ferrite (bright) and perlite (dark), which is a characteristic of iron with < 0.8 % C. (magnification = 20 ×).




Figure 8: Iron flange of coin 4 as etched with Nital. View towards the edge of the coin, where needle-like ferrite-perlite structure developed, which forms when hypo-eutectic Fe-C with < 0.8 % C was overheated (magnification = 20 ×).

3.3. The copper layer

The copper layer of coin 4 is homogeneously 0.4–0.3 mm thick (*Fig. 9*). Copper has no microstructural relation to the iron flange. The interface is sharp and there is no material exchange. The adhesion of the copper metal to the iron is without solvent and also without bonding layer and therefore of high quality. The close bond protects the iron from oxidation and corrosion. In the copper layer, dendritic or spherical iron is homogeneously distributed as a metal throughout it (*Fig. 10*). The presence of iron in the metallic state is strongly supported by observation with SEM, where the iron inclusions appear with exactly the same brightness as the metallic iron flange. Iron oxide or silicate phase would appear darker than the iron flange in a backscattered image. Theoretically iron has a limited solubility in copper. Iron can reach 2.8 % in at 1010 °C (s) melting temperature in the copper, and can rise continuously up to 20 % at 1400 °C⁵⁷.

⁵⁷ CRADDOCK – MEEKS 1987; Smelting temperatures of pure copper: 1085,5 °C, of pure iron: 1535°C. Taking-up rate of iron in copper see phase diagram Fe-Cu (<http://www.ams.org.cn/article/2014/0895-3988-1224/grp1E39.jpg.html>)




Figure 9: Polarized microscope, cross polished section of the subferrate coin 4 as polished. Core (blue) = iron flan, layer (brown/blue) = copper layer. The thickness of the copper layer is 300–350 µm.




Figure 10: Polished section of subferrate coin 4. The coin is diagonally oriented in the image. Interface between iron flan and copper layer. Left: Iron flan (in blue), right is the copper layer (beige), in which dendritic α -iron (blue) is distributed homogeneously throughout the copper layer, but iron and copper is not in interfacial exchange between the two materials. The interface between iron and copper is sharp with the iron flan being passively protected from corrosion by the covering copper layer. The joint is very tight without any oxidation occurring. No solder has been used either.

Sectional images are presented in the literature⁵⁸ as etched demonstrating that their iron flan was a low carbon steel with 0.15 % which was heated to about 1000 °C. It was suggested that at this temperature molten iron could dissolve in the copper metal. Deformation twins (Neumann lines) in the microstructure of an iron core are suggested to indicate that the embossing was performed after cooling of the flan⁵⁹. The technique of dipping the iron flan in molten (copper) metal was confirmed for their example. Backscattered images of “drop-shaped iron precipitates in copper plating”⁶⁰ occur very close to the interface between coating and core. They are caused by the interaction between the molten copper (alloy) and the iron flan when iron droplets from the flan enter the copper (alloy) layer. This would require that the iron flan at least melts superficially to move as droplets into the molten copper (alloy), but only indicates operating temperatures around the melting point of the copper alloy which would not exceed

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate *asses* of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

58 ZWICKER – DEMBSKI 1988, p. 16
Fig. 2.3.

59 HAUBNER et al. 2016.

60 HAUBNER et al. 2016, p. 450.

S. Klein, H.-M. von Kaenel: Chemical and isotopic characterization and production technique of sub-ferrite *asses* of the Lyons Altar series, SM 70, 2020, S. 3–21.

1030 °C and thus would not reach the required temperature level to move the iron in the molten state. Alternatively, solid-state reaction diffusion⁶¹ is described as a process in which iron moves from the solid flan into the coating melt (alloy) forming a so-called diffusion zone. The latter phenomenon is explicitly explained as a solid iron-melt-copper reaction, and many images can be found in the literature to visualize the interfacial diffusion effects. It is underlined by a description of iron that is “*interfaced to copper at the bottom by way of dendritic... iron*”⁶².

In contrast to these descriptions, the appearance of the iron inclusions in the copper layer of coin 4 differs from such observations and earlier published images⁶³, as the iron does not spread from the iron flan into the copper layer and is not an enriched zone at the interface of the two. The presence of spheroid and dendritic α -iron therefore cannot be interpreted as exchanged and detached from the underlying iron or as diffused into the (molten) copper during the coating process. Another explanation made in literature that stirring with an iron rod in molten copper would introduce iron into copper metal⁶⁴ is not a reasonable explanation here, because it seems inappropriate to us that the melting temperature of iron was reached for the coating process that would have been required for melting iron from the stirring rod into the copper.

Another explanation for the presence of metallic iron in the copper layer concerns surface chips as residues from the forging process of the iron flan (iron scale), which contaminate the iron flan surface and are thus introduced into the (molten) copper layer if the iron surface has not been thoroughly cleaned prior to the coating process⁶⁵. This does not apply here either, because scale residues would appear sharp-edged by the mechanical process, but never dendritic or spherical.

Only at the edges of coin 4 do fractions occur in the copper layer which are sharp and ragged. Here, in contrast to the ob- and revers planes, the corrosion only penetrates deep into the iron flan. The iron flan is significantly dented here (*Fig. 11*), which indicates that intensive stress particularly affected this area of the flan.




Figure 11: Coin 4. One of the two barrel-shaped edges of coin 4. The iron flan is significantly dented and the barrel shape is distorted. Where the copper sheet has broken apart, the iron flan is weakened and in consequence heavily corroded. The copper layer appears as cut surfaces.

61 ZWICKER – DEMBSKI 1988, p. 15.

62 ISHIDA 1986, Fig. 8; s. also CRADDOCK – MEEKS 1987, p. 199.

63 PINTZ 2014, p. 219; HAUBNER et al. 2016, pp. 448–449; ZWICKER – DEMBSKI 1988, p. 16. Varieties in copper plating composition is reported, gun-metal, a Cu-Pb-Sn-Zn leaded red brass.

64 COOKE – ASCHENBRENNER 1975, p. 253.

65 pers. comm. R. Traum, March 14, 2017.

Etching the copper layer of the subferrate coin reveals the laminar structure with compressed and elongated grains parallel to the iron flan planes. No annealing twins or slip lines can be observed, so that cold forming is indicated as the process used. Around the edges of the subferrate coin, the microstructure is dominated by more equiaxed grains (*Fig. 12*). Remembered is the etched microstructure of the iron flan at the edges, which indicates overheating. The overheated microstructure is discussed in context to subaerate/subferrate coins as a consequence of applying a wrapping sheet with subsequent and slight heating to bond the metals⁶⁶.

This reinforces the fact that the ob- and reverse planes of the coin had passed through different temperature conditions and stress than the edges from the coating and joining process, which had affected the edges more than the ob- and reverse planes. Also, the laminar structure resulting from cold working of the copper layer along the planes can be considered as an effect of the striking procedure.




Figure 12: Backscattered image (EPMA). Microstructure of the copper layer on the plane sides of the coin (laminar structure) is different from the edges (equiaxed structure).

Acknowledgements

Our thanks go at first to the finders of the coins, Jörg Lotter and Michael Paulsen, and to Thomas Becker from the Abteilung hessenARCHÄOLOGIE des Landesamtes für Denkmalpflege Hessen, Aussenstelle Darmstadt, who supported us just as Markus Helfert, Karlheinz Engemann, Thomas Maurer and Markus Scholz. For numismatic advice we are grateful to Nathan T. Elkins, Michael Nick and Markus Peter. Peter Northover made helpful comments concerning our metallographic interpretation. We would like to thank René Traum, Kunsthistorisches Museum Wien, for providing one of his flans, an experimental product, for investigating the joining techniques of subferrate coins. FIERCE is financially supported by the Wilhelm and Else Heraeus Foundation and by the Deutsche Forschungsgemeinschaft (DFG, INST 161/921-1 FUGG and INST 161/923-1 FUGG), which is gratefully acknowledged. This is FIERCE contribution No. 12. Andreas Ludwig (DBM) has helped with the preparation of the polished speci-

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate asses of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

66 SCOTT – SCHWAB 2019; ANHEUSER – NORTHOVER 1994, p. 30: “... to plate their cores, the Romans wrapped them in pure silver foil and heated them rapidly to close to the melting point of silver for a short time, no more than a few minutes.”

S. Klein, H.-M. von Kaenel:
Chemical and isotopic
characterization and pro-
duction technique of sub-
ferrate *asses* of the Lyons
Altar series, SM 70, 2020,
S. 3–21.

men and Dirk Kirchner (DBM) operated the REM. We are grateful for Samuel Nussbaum's and Ruedi Kunzmann's editorial support.

Photographic credits: Coins 1, 4 were made with a photographic instrument of the Römisch-Germanische Kommission (RGK), Frankfurt a. M. We thank J. Lotter for the photograph of coin 2, and M. Paulsen for coin 3.

Translation and language improvement were partly undertaken with www.DeepL.com/Translator (free version).

Sabine Klein (Metallurgie, Analytik, Technik)
Forschungsbereich Archäometallurgie
Deutsches Bergbau-Museum Bochum
Am Bergbaumuseum 31
44791 Bochum, Germany
sabine.klein@bergbaumuseum.de

and also

Frankfurt Isotope and Element Research Center (FIERCE)
Goethe-Universität Frankfurt am Main
60438 Frankfurt am Main, Germany

Hans-Markus von Kaenel (Archäologie, Numismatik)
Goethe-Universität Frankfurt am Main
Institut für Archäologische Wissenschaften, Abt. II
Norbert-Wollheim-Platz 1
60629 Frankfurt am Main, Germany
v.kaenel@em.uni-frankfurt.de

References Part I

- AARTS et al. 2009
J. AARTS – N. ROYMANS, Tribal emission or imperial coinage? Ideas about the production and circulation of the so-called AVAVCIA coinages in the Rhineland, in: J. VAN HEESCH – I. HEEREN (eds.), *Coinage in the Iron Age: Essays in Honour of Simone Scheers* (London 2009), pp. 1–17.
- VAN ALFEN 2005
P. G. VAN ALFEN, Problems in Ancient Imitative and Counterfeit Coinage, in: Z. H. ARCHIBALD – J. K. DAVIS – V. GABRIELSEN (eds.), *Making, Moving and Managing. The New World of Ancient Economies* (Oxford 2005), pp. 322–354.
- ANHEUSER 1998
K. ANHEUSER, Silver-Plated-on-Iron Roman Coins, in: W. A. ODDY – M. R. COWELL (eds.), *Metallurgy in Numismatics 4*, Royal Numismatic Society Special Publication 30 (London 1998), pp. 134–146.
- ANHEUSER – NORTHOVER 1994
K. ANHEUSER – P. NORTHOVER, Silver Plating on Roman and Celtic Coins from Britain - A Technical Study, *The British Numismatic Journal* 64, 1994, pp. 22–32.
- ARBABE 2017
E. ARBABE, La politique des Gaulois: Vie politique et institutions en Gaule chevelue (II^e siècle avant notre ère – 70), *Histoire ancienne et médiévale* 150, Université Paris 1 Panthéon-Sorbonne (Paris 2017).
- BARRANDON et al. 2010
J.-N. BARRANDON – A. SUSPÈNE – A. GAFFIERO, Les émissions d'as au type *Divvus Avgvstvs Pater* frappées sous Tibère: L'apport des analyses à leur datation et à leur interprétation, *RN* 2010, pp. 149–173.
- BERGER 1996
F. BERGER, Kalkriese 1: Die römischen Fundmünzen, *Römisch-Germanische Forschungen* 55 (Mainz 1996).
- BURKHARDT 1989
A. BURKHARDT, *Quantitative Methoden zur keltischen Numismatik am Beispiel der Münzfunde aus latènezeitlichen Siedlungen der Oberrheinregion*. Dissertation Universität Basel 1986 (Bern 1998).
- BURMEISTER – ORTISI (eds.) 2018
ST. BURMEISTER – S. ORTISI (eds.), *Phantom Germanicus. Spurensuche zwischen historischer Überlieferung und archäologischem Befund*. Symposium vom 2.–3. Juli 2015 Museum und Park Kalkriese/Universität Osnabrück, *Materialhefte zur Ur- und Frühgeschichte Niedersachsens* 53 (Rahden/Westf. 2018).
- COOKE – ASCHENBRENNER 1975
ST. R. B. COOKE – ST. ASCHENBRENNER, The Occurrence of Metallic Iron in Ancient Copper, *Journal of Field Archaeology* 2, 3, 1975, pp. 251–266 (DOI: 10.1179/009346975791491015).
- CRADDOCK – MEEKS 1987
P. T. CRADDOCK – N. D. MEEKS, Iron in Ancient Copper, *Archaeometry* 29, 2, 1987, pp. 187–204 (DOI: <https://doi.org/10.1111/j.1475-4754.1987.tb00411.x>).
- CRAWFORD 1968
M. H. CRAWFORD, Plated coins – false coins, *NC* 1968, pp. 55–59.
- CRAWFORD 1985
M. H. CRAWFORD, *Coinage and Money under the Roman Republic. Italy and the Mediterranean Economy* (London 1985).
- DEBERNARDI 2010
P. DEBERNARDI, Plated coins, false coins?, *RN* 2010, pp. 337–381 (DOI: 10.3406/numi.2010.2941).
- DELESTRÉE 2017
L.-P. DELESTRÉE, Les pouvoirs émetteurs en Gaule des origines à l'époque augustéenne, *RBN* 163, 2017, pp. 1–26.
- DEMBSKI 1993
G. DEMBSKI, Römisches Notgeld in Noricum und Pannonien, *RIN* 95, 1993, pp. 453–460.
- S. Klein, H.-M. von Kaenel:
Chemical and isotopic characterization and production technique of sub-ferrate *asses* of the Lyons Altar series, *SM* 70, 2020, S. 3–21.

S. Klein, H.-M. von Kaenel: Chemical and isotopic characterization and production technique of sub-ferrate *asses* of the Lyons Altar series, *SM* 70, 2020, S. 3–21.

DONDIN-PAYRE 1999

M. DONDIN-PAYRE, Magistratures et administration municipale dans les Trois Gaules, in: M. DONDIN-PAYRE – M.-Th. RAEPSAET-CHARLIER (eds.), *Cités, Municipales, Colonies. Les processus de municipalisation en Gaule et en Germanie sous le Haut Empire romain* (Paris 1999), pp. 127–230.

DOYEN 2007

J.-M. DOYEN, Économie, monnaie et société sous l'Empire Romain. Recherches sur la circulation monétaire en Gaule septentrionale intérieure, *Bulletin de la Société archéologique champenoise* 100 (Reims 2007).

DOYEN et al. 2017

J.-M. DOYEN – ST. MARTIN – M. PETER (eds.), Les monnaies de bronze à « âme de fer » (*nummi subferrati*) dans les provinces occidentales continentales de l'Empire Romain (Gaules, Germanies, Rhétie, Norique), *The Journal of Archaeological Numismatics* 7, 2017, pp. 201–297.

GIARD 1970

J.-B. GIARD, La pénurie de petite monnaie en Gaule au début du Haut-Empire, *Journal des Savants* Avril-Juin 1975, pp. 81–112.

GIARD 1983

J.-B. GIARD, Le monnayage de l'atelier de Lyon des origines au règne de Caligula (43 avant J.-C. – 41 après J.-C.), *Numismatique Romaine* 14 (Wetteren 1983).

HAUBNER et al. 2016

R. HAUBNER – S. STROBL – J. ZBIRAL – C. GUSENBAUER – U. PINTZ, Metallurgical Characterization of a coated Roman Iron Coin by Analytical Investigations, *Archaeometry* 58, 3, 2016, pp. 441–452 (DOI: 10.1111/arcm.12179).

VAN HEESCH 1987

J. VAN HEESCH, Bronzes romains à âme de fer, *Bulletin Cercle d'Études Numismatiques* 24, 3, 1987, pp. 53–65.

VAN HEESCH 1993

J. VAN HEESCH, Proposition d'une nouvelle datation des monnaies en bronze à l'autel de Lyon frappées sous Auguste, *BSFN* 48, 1993, pp. 535–538.

VAN HEESCH 2005

J. VAN HEESCH, Les Romains et la monnaie gauloise: laisser-faire, laisser-aller?, in: J. METZLER – D. WIGG-WOLF (eds.), *Die Kelten und Rom: Neue numismatische Forschungen. Kolloquium Fond du Gras/Titelberg, Luxemburg, 30.4. – 3.5.1998, SFMA 19* (Mainz 2005), pp. 234–245.

VAN HEESCH 2009

J. VAN HEESCH, Providing markets with samll change in the early Roman Empire: Italy and Gaul, *RBN* 155, 2009, pp. 125–141.

ILISCH 1999

P. ILISCH, Die Münzen aus den römischen Militäranlagen in Westfalen, in: W. SCHLÜTER – R. WIEGELS (eds.), *Rom, Germanien und die Ausgrabungen von Kalkriese. Internationaler Kongress der Universität Osnabrück und des Landschaftsverbandes Osnabrücker Land e. V. vom 2.–5. September 1996, Osnabrücker Forschungen zu Altertum und Antike-Rezeption 1* (Osnabrück 1999), pp. 279–291.

ISHIDA 1986

T. ISHIDA, The interaction of molten copper with solid iron, *Journal of Material Science* 21, 1986, pp. 1171–1179.

KEMMERS – SCHOLZ 2017

F. KEMMERS – M. SCHOLZ, Ein spezifischer Wert: ein republikanischer Denar mit Graffiti aus Gross-Rohrheim, in: U. RECKER (ed.), *lucundi acti labores. Festschrift für E. Schallmayer, hessenARCHÄOLOGIE Sonderband 5* (Stuttgart 2017), pp. 124–128.

KLEIN – VON KAENEL 2000

S. KLEIN – H.-M. VON KAENEL, The early Roman Imperial *AES* Coinage I: Metal Analysis and Numismatic Studies: The Chemical Profile of Copper Coins of the Rome Mint from Augustus to Claudius, *SNR* 79, 2000, pp. 53–106.

KLEIN et al. 2004

S. KLEIN – Y. LAHAYE – G.P. BREY – H.-M. VON KAENEL, The early Roman Imperial *AES* Coinage II: Tracing the copper sources by analysis of lead and copper isotopes – copper coins of Augustus and Tiberius, *Archaeometry* 46, 3, 2004, pp. 469–480 (DOI: 10.1111/j.1475-4754.2004.00168.x).

KLEIN et al. 2012

S. KLEIN – H.-M. VON KAENEL – Y. LAHAYE – G.P. BREY, The early Roman Imperial *AES* Coinage III: Chemical and isotopic characterization of Augustan copper coins from the mint of Lyons/Lugdunum, *SNR* 91, 2012, pp. 63–110.

KOMNICK 2015

H. KOMNICK, Die Fundmünzen der römischen Zeit aus dem Bereich der Colonia Ulpia Traiana. *Xantener Berichte* 29 (Darmstadt 2015).

DE LIGHT 2009

L. DE LIGHT, From the Tax-Payer to the Roman treasury: Three case studies, *RBN* 155, 2009, pp. 81–90.

MARTIN 2011

ST. MARTIN, Monnaies romaines, usagers gaulois et vice versa. L'exemple de la Gaule de l'Est, in: M. REDDÉ (ed.), *Aspects de la Romanisation dans l'Est de la Gaule* 2, Collection *Bibracte* 21 (Glux-en-Glenne 2011), pp. 937–944.

MARTIN 2015

ST. MARTIN, Du statère au sesterce. Monnaie et romanisation dans la Gaule du Nord et de l'Est (III^e s. a. C./I^{er} s. p. C.), *Scripta Antiqua* 78 (Bordeaux 2015).

MARTIN 2018

ST. MARTIN, Germanicus on the Upper-Rhine. Later Augustan and early Tiberian contexts from *Germania Superior*, in: BURMEISTER – ORTISI (eds.) 2018, pp. 253–272.

MAURER 2011

T. MAURER, Das nördliche Hessische Ried in römischer Zeit. Untersuchungen zur Landschafts- und Siedlungsgeschichte im rechtsrheinischen Vorfeld von Mainz vom 1. bis 5. Jahrhundert n. Chr, *Frankfurter Archäologische Schriften* 14 (Bonn 2011).

MOESTA – FRANKE 1995

H. MOESTA – P.R. FRANKE, *Antike Metallurgie und Münzprägung. Ein Beitrag zur Technikgeschichte* (Basel 1995).

NÜSSE 2014

M. NÜSSE, Metal analysis of local imitations of early Roman imperial *asses* found in the Gallo-Roman sanctuary on the Martberg in the Mosel valley, *SM H.* 255, 2014, pp. 75–84.

OLSEN et al. 2020

S. OLSEN – F. SILVEMINI – V. LUZIN – U. GARBE – M. AVDEEV – J. DAVIS – K. SHEEDY, A Neutron Tomographic Analysis of Plated Silver Coins from Ancient Greece Official or Illegal?, *Materials Research Proceedings* 15, 2020, pp. 233–38 (DOI: <https://doi.org/10.21741/97816444900574-36>).

PETER 1996

M. PETER, *Augsta Raurica I. Augst 1949–1972*, *IFS* 3 (Lausanne 1996).

PETER 2001

M. PETER, Untersuchungen zu den Fundmünzen aus Augst und Kaiseraugst, *SFMA* 17 (Berlin 2001).

PETER 2004

M. PETER, Imitation und Fälschung in römischer Zeit, in: A. F. AUBERSON – H. R. DERSCHKA – S. FREY-KUPPER (eds.), *Fälschungen – Beischnläge – Imitationen. Sitzungsbericht des vierten internationalen Kolloquiums der Schweizerischen Arbeitsgemeinschaft für Fundmünzen* (Martigny, 1.–2. März 2002). *Untersuchungen zu Numismatik und Geldgeschichte* 5 (Lausanne 2004), pp. 19–30.

PETER 2011

M. PETER, Von Betrug bis Ersatzkleingeld – Falschmünzerei in römischer Zeit, in: M. REUTER – R. SCHIAVONE (eds.), *Gefährliches Pflaster. Kriminalität im Römischen Reich*. *Xantener Berichte* 21 (Mainz 2011), pp. 107–119.

PFISTERER 2006

M. PFISTERER, *Limesfalsa und subferrate Kleingeldkopien: Römischer Ersatzgeld am Donaulimes*, Dissertation Universität Wien 2006.

S. Klein, H.-M. von Kaenel:

Chemical and isotopic characterization and production technique of subferrate *asses* of the Lyons Altar series, *SM* 70, 2020, S. 3–21.

S. Klein, H.-M. von Kaenel: Chemical and isotopic characterization and production technique of subferrate asses of the Lyons Altar series, *SM* 70, 2020, S. 3–21.

PFISTERER 2007a

M. PFISTERER, Falschgeld und Beischläge der Prinzipatszeit in Carnuntum – Ein Überblick, in: M. ALRAM – F. SCHMIDT-DICK (eds.), *Numismata Carnuntina. Forschungen und Material. Die Fundmünzen der Römischen Zeit in Österreich*, Abt. III, Niederösterreich 2, Die antiken Fundmünzen im Museum Carnuntinum. Österreichische Akademie der Wissenschaften (Wien 2007), pp. 635–642.

PFISTERER 2007b

M. PFISTERER, Limesfalsa und Eisenmünzen – Römischer Ersatzkleingeld am Donaulimes, in: M. ALRAM – F. SCHMIDT-DICK (eds.), *Numismata Carnuntina. Forschungen und Material. Die Fundmünzen der Römischen Zeit in Österreich*, Abt. III, Niederösterreich 2, Die antiken Fundmünzen im Museum Carnuntinum, Österreichische Akademie der Wissenschaften (Wien 2007), pp. 643–875.

PFISTERER – TRAUM 2005a

M. PFISTERER – R. TRAUM, Die Herstellungstechnik subferrater Kopien römischer Buntmetallmünzen: ein praktisches Experiment, *SNR* 84, 2005, pp. 125–140 (DOI: <http://doi.org/10.5169/seals-175930>).

PFISTERER – TRAUM 2005b

M. PFISTERER – R. TRAUM, Ein Experiment zur römischen Falschmünzertechnik, *Technologische Studien* 2, 2005, pp. 72–85.

PINTZ 2014

U. PINTZ, *FMRÖ Salzburg – Die Fundmünzen der Villa Loig und ihre Besonderheit, die Eisenmünzen*, Dissertation Universität Wien 2014.

SAUER 2005

E. SAUER, *Coins, cult and cultural identity: Augustan coins, hot springs and the early Roman baths at Bourbonne-les-Bains*, *Leicester Archaeology Monographs* 10 (Leicester 2005).

SCHEERS 1983

S. SCHEERS, *La Gaule Belgique. Numismatique celtique*² (Louvain 1983).

SCOTT – SCHWAB 2019

D. SCOTT – R. SCHWAB, *Metallography in Archaeology and Art*, Springer International Publishing 2019.

THIRION 1975

M. THIRION, *Bronzes romains à âme de fer trouvés en Belgique*, *Bulletin Cercle d'Études Numismatiques* 12, 3, 1975, pp. 41–44.64–65.

WERZ 2018a

U. WERZ, Die neugefundenen Aurei von Kalkriese. Erste Einordnung, in: R. LEHMANN – K. HAGEMANN – H. HASSMANN (eds.), *Von Drusus bis Maximinus Thrax – Römer in Norddeutschland. Festschrift zum achtzigsten Geburtstag von Wilhelm Dräger*, *Schriftenreihe des Freundeskreises für Archäologie in Niedersachsen e. V. (FAN) 1* (Hannover 2018), pp. 50–67.

WERZ 2018b

U. WERZ, Gibt es einen «Germanicus-Horizont» im Fundmünzaufkommen?, in: BURMEISTER – ORTISI (eds.), pp. 221–236.

WIGG-WOLF 1996

D. WIGG-WOLF, The function of the latest Celtic coinages in Northern Gaul, in: C. E. KING – D. WIGG-WOLF (eds.), *Coin Finds and Coin Use in the Roman World. The Thirteenth Oxford Symposium on Coinage and Money History*, 25.–17.3.1993, *SFMA* 10 (Berlin 1996), pp. 415–436.

WIGG-WOLF 2004

D. G. WIGG-WOLF, Zur Interpretation und Bedeutung der «Barbarisierungen» der römischen Kaiserzeit, in: A. F. AUBERSON – H. R. DERSCHKA – S. FREY-KUPPER (eds.), *Fälschung – Beischläge – Imitationen. Sitzungsbericht des vierten internationalen Kolloquiums der Schweizerischen Arbeitsgemeinschaft für Fundmünzen* (Martigny, 1.–2. März 2002). *Untersuchungen zu Numismatik und Geldgeschichte* 5 (Lausanne 2004), pp. 55–75.

WIGG-WOLF 2018

D. WIGG-WOLF, 9 or not 9? New thoughts on Waldgirmes, Haltern, Kalkriese and co., in: BURMEISTER – ORTISI (eds.), pp. 237–252.

WOLTERS 2002

R. WOLTERS, Gaius und Lucius Caesar als designierte Konsuln und principes iuventutis. Die lex Valeria Cornelia und RIC I² 205 ff., *Chiron* 32, 2002, pp. 297–323.

WOLTERS 2017

R. WOLTERS, Von der Vielfalt zur Einheit. Münzbilder und Prägemen gen auf dem Wege zur Monarchie., in: M. FLECKER – St. KRMNICEK – J. LIPPS – R. POSAMENTIR – Th. SCHÄFER (eds.), Augustus ist tot – Lang lebe der Kaiser! Internationales Kolloquium anlässlich des 2000. Todesjahres der römischen Kaisers vom 20.–22. November 2014 in Tübingen. Tübinger Archäologische Forschungen 24 (Rahden/Westf. 2017), pp. 41–61.

WOLTERS 2018

R. WOLTERS, Zwischen VAR(us) und Germanicus: Die spätesten Kontermarken auf den Buntmetallmünzen von Kalkriese, in: BURMEISTER – ORTISI (eds.) 2018, pp. 273–318.

WOYTEK – BLET-LEMARQUAND 2017

B. WOYTEK – M. BLET-LEMARQUAND, The C. L. CAESARES denarii RIC I² Augustus 208. A pseudo-Augustan unsigned restoration issue. Corpus, die study, metalurgical analyses, RN 2017, pp. 183–248.

ZEDELIUS 1988

V. ZEDELIUS, Nummi subferrati, RIN 90, 1988, pp. 125–130.

ZEHNACKER et al. 1984

H. ZEHNACKER – J.-Cl. RICHARD – J.-N. BARRANDON, La trouvaille de la Villeneuve-au-Châtelot (Aube), Trésors Monétaires 6 (Paris 1984), pp. 9–92.

ZWICKER et al. 1993

U. ZWICKER – A. ODDY – S. LA NIECE, Roman techniques of manufacturing silver-plated coins, in: S. LA NIECE – P. CRADDOCK (eds.), Metal Plating and Patination - Cultural, Technical and Historical Developments (Oxford 1993), pp. 223–246.

ZWICKER – DEMBSKI 1988

U. ZWICKER – G. DEMBSKI, Technisch-chemische Untersuchungen an subferraten Sesterzen, Mitteilungen der Österreichischen Numismatischen Gesellschaft 28, 1988, pp. 12–17.

S. Klein, H.-M. von Kaenel:

Chemical and isotopic characterization and production technique of subferrate *asses* of the Lyons Altar series, SM 70, 2020, S. 3–21.